

【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site
URL : <https://www.asahi-kasei-plastics.com/en/contact/>

AsahiKASEI



TENAC™-C TFC64

Asahi Kasei Corporation - Acetal (POM) Copolymer

Wednesday, March 20, 2024

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features AKEP website	• Electrically Conductive		
Uses	• Bearings • Engineering Parts	• Gears • Housings	
Part Marking Code (ISO11469) (ISO 11469)	• >POM-CD<		

Other Documentation

Literature	• Molding Conditions • SDS • Technical Handbook
------------	---

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.37	g/cm ³	ASTM D792 ISO 1183
Molding Shrinkage - Flow	1.3 to 1.6	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-1
Tensile Stress			
Break	35.0	MPa	ISO 527-2
--	33.0	MPa	ASTM D638
Tensile Elongation			
Break	3.0	%	ASTM D638
Break	2.0	%	ISO 527-2
Flexural Modulus			
--	2010	MPa	ASTM D790
--	2100	MPa	ISO 178
Flexural Strength	63.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.5	kJ/m ²	ISO 179
Notched Izod Impact	33	J/m	ASTM D256

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

TENAC™-C TFC64**Asahi Kasei Corporation - Acetal (POM) Copolymer**

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	160	°C	ASTM D648
0.45 MPa, Unannealed	146	°C	ISO 75-2/B
1.8 MPa, Unannealed	123	°C	ASTM D648
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0 to 1.0E+2	ohms	ASTM D257
--	1.0 to 10	ohms	JIS K7194 IEC 60093
Volume Resistivity			
--	1.0 to 1.0E+2	ohms·cm	ASTM D257
--	1.0 to 10	ohms·cm	JIS K7194 IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80 to 90	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Processing (Melt) Temp	180 to 210	°C
Mold Temperature	> 60	°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.