

## 【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site

URL : <https://www.asahi-kasei-plastics.com/en/contact/>

# AsahiKASEI



## XYRON™ G402H

Asahi Kasei Corporation - Polyphenylene Ether + PS

Wednesday, February 28, 2024

### General Information

#### Product Description

Modified PPE

20% Filler reinforced Non-Flame retardant

#### General

Material Status

• Commercial: Active

Availability

• Africa & Middle East  
• Asia Pacific• Europe  
• North America

Filler / Reinforcement

• Glass Fiber, 20% Filler by Weight

Processing Method

• Injection Molding

Part Marking Code (ISO11469) (ISO 11469)

• &gt;PPE+PS-GF20&lt;

#### Other Documentation

Literature

• [Moldflow Data](#)  
• [Molding Conditions](#)  
• [SDS](#)  
• [Technical Handbook](#)

### ASTM & ISO Properties<sup>1</sup>

| Physical                                           | Nominal Value | Unit              | Test Method     |
|----------------------------------------------------|---------------|-------------------|-----------------|
| Density                                            | 1.19          | g/cm <sup>3</sup> | ISO 1183        |
| Molding Shrinkage <sup>2</sup> (2.00 mm)           | 0.23 to 0.50  | %                 | Internal Method |
| Mechanical                                         | Nominal Value | Unit              | Test Method     |
| Tensile Stress (Yield, 23°C)                       | 95.0          | MPa               | ISO 527         |
| Tensile Strain (Break, 23°C)                       | 2.0           | %                 | ISO 527         |
| Flexural Modulus (23°C)                            | 6900          | MPa               | ISO 178         |
| Flexural Stress (23°C)                             | 158           | MPa               | ISO 178         |
| Impact                                             | Nominal Value | Unit              | Test Method     |
| Charpy Notched Impact Strength <sup>3</sup> (23°C) | 11            | kJ/m <sup>2</sup> | ISO 179         |
| Thermal                                            | Nominal Value | Unit              | Test Method     |
| Deflection Temperature Under Load                  |               |                   | ISO 75-2/A      |
| 1.8 MPa, Unannealed                                | 113           | °C                |                 |
| CLTE                                               |               |                   | ISO 11359-2     |
| Flow : -30 to 65°C                                 | 3.2E-5        | cm/cm/°C          |                 |
| Transverse : -30 to 65°C                           | 7.5E-5        | cm/cm/°C          |                 |

#### Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

**XYRON™ G402H****Asahi Kasei Corporation - Polyphenylene Ether + PS**

| Electrical                     | Nominal Value | Unit    | Test Method |
|--------------------------------|---------------|---------|-------------|
| Surface Resistivity            | 1.0E+16       | ohms    | IEC 60093   |
| Volume Resistivity (23°C)      | 1.0E+16       | ohms·cm | IEC 60093   |
| Dielectric Constant (5.20 GHz) | 2.90          |         | SPDR        |
| Dissipation Factor (5.20 GHz)  | 3.0E-3        |         | SPDR        |
| Flammability                   | Nominal Value | Unit    | Test Method |
| Flame Rating (1.5 mm)          | HB            |         | UL 94       |

**Processing Information**

| Injection                          | Nominal Value | Unit |
|------------------------------------|---------------|------|
| Drying Temperature - Hot Air Dryer | 90 to 100     | °C   |
| Drying Time - Hot Air Dryer        | 2.0 to 4.0    | hr   |
| Processing (Melt) Temp             | 240 to 300    | °C   |
| Mold Temperature                   | 50 to 80      | °C   |

**Notes**<sup>1</sup> Typical properties: these are not to be construed as specifications.<sup>2</sup> 150x150x2 mm<sup>3</sup> 4 mm**Disclaimer:**

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.