

Product Information

Jan 2016

Ultradur® B 4520 BK00110 **PBT (Polybutylene Terephthalate)**


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultradur B 4520 BK00110 is a medium viscosity, pigmented black, rapidly freezing injection molding grade.

Applications

Typical applications include chassis and housings for home appliances, office and sewing machines, and coil formers.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm ³	1183	1.3
Viscosity Number, cm ² /g	1628	119
Moisture, %	62	
(50% RH)		0.25
(Saturation)		0.5
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23°C		2,400
Tensile stress at yield, MPa	527	
23°C		57
Tensile strain at yield, %	527	
23°C		3.5
Nominal strain at break, %	527	
23°C		15
Flexural Modulus, MPa	178	
23°C		2,500
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m ²	180	
-40°C		4.2
23°C		4.8
Charpy Notched, kJ/m ²	179	
23°C		5
THERMAL	ISO Test Method	Property Value
Melting Point, °C	3146	223
HDT A, °C	75	55
HDT B, °C	75	132
UL RATINGS	UL Test Method	Property Value
Flammability Rating, 0.75mm	UL94	HB
Relative Temperature Index, 0.75mm	UL746B	
Mechanical w/o Impact, °C		140
Mechanical w/ Impact, °C		130
Electrical, °C		130
Flammability Rating, 1.5mm	UL94	HB
Relative Temperature Index, 1.5mm	UL746B	
Mechanical w/o Impact, °C		140
Mechanical w/ Impact, °C		130
Electrical, °C		130
Flammability Rating, 2.8mm	UL94	HB
Relative Temperature Index, 2.8mm	UL746B	
Mechanical w/o Impact, °C		140
Mechanical w/ Impact, °C		130
Electrical, °C		130

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

