

Product Information Ultraform®**Z2320 003**

08/2012

POM**Product description**

Extremely easy flowing grade for very thin-walled moldings with difficult flow path to wall thickness ratios and very short cycle times.

Abbreviated designation according to ISO 1043: POM
Designation according to ISO 9988-1: POM-K, M-GNR, 06-002

Physical form and storage

Ultraform® is supplied in the form of granules having a bulk density of approx. 850 g/l. Standards packs are the 25 kg PE bag and the 1000 kg Oktabin (octagonal container). Ultraform® is not subject to change when it is stored in dry, ventilated rooms. After relatively long storage (>1 year) or when handling material from previously opened containers, preliminary drying is recommended in order to remove any moisture which has been absorbed.

Product safety

Ultraform® is not a hazardous material as defined in the German Ordinance on Hazardous Materials.

If Ultraform® is processed properly little or no formaldehyde occurs in the region of the processing machine. Measures should be taken to ensure ventilation and venting of the work area, preferably by means of an extraction hood over the barrel unit.

Ultraform® decomposes when subjected to excessive heat. The decomposition products formed in this case consist almost exclusively of formaldehyde, a gas which has a pungent smell even at very low concentrations and irritates the mucous membranes. Decomposition can rapidly result in the build-up of a high gas pressure in the barrel of the processing unit. If the die is sealed there may be a sudden release of pressure via the filling hopper.

Contamination of Ultraform® by thermoplastics that cause decomposition of polyacetals, e.g. PVC or plastics containing halogenated fire protection agents, must be avoided under all circumstances. Even small quantities can cause uncontrolled and rapid decomposition of Ultraform® during processing.

Pellets and finished parts must not be allowed to come into contact with strong acids (especially concentrated hydrochloric acid) since they cause Ultraform® to decompose.

Detailed safety and environmental information is contained in the Ultraform® brochure and the material safety data sheet. Both are available from the PlasticsPortal, www.plasticsportal.net, or the Ultra-Infopoint under phone +49-621-60-78780 or fax +49-621-60-78730.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultraform® Z2320 003



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method ²⁾	Unit	Values ³⁾
Properties			
Polymer abbreviation	-	-	POM
Density	ISO 1183	kg/m ³	1400
Water absorption, equilibrium in water at 23°C	similar to ISO 62	%	0.8
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	0.20
Processing			
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	M
Melting temperature, DSC	ISO 11357-1/-3	°C	166
Melt volume-flow rate MVR at 190 °C and 2.16 kg	ISO 1133	cm ³ /10min	42
Melt temperature, injection moulding	-	°C	190 - 230
Mould temperature, injection moulding	-	°C	60 - 120
Molding shrinkage (parallel)	ISO 2577, 294-4	%	2.00
Molding shrinkage (normal)	ISO 2577, 294-4	%	2.10
Flammability			
UL94 rating at 1,6 mm thickness	IEC 60695-11-10	class	HB
Automotive materials (thickness d >= 1mm)	FMVSS 302	-	+
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	2800
Yield stress, 50 mm/min	ISO 527-1/-2	MPa	65
Yield strain, 50 mm/min	ISO 527-1/-2	%	7
Nominal strain at break, 50 mm/min	ISO 527-1/-2	%	20
Tensile creep modulus, 1000 h, strain <= 0,5%, 23°C	ISO 899-1	MPa	1350
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	130
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	130
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	5.5
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	4.5
Ball indentation hardness at 358 N and 30 s	ISO 2039-1	MPa	150
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	105
Max. service temperature (short cycle operation)	-	°C	100
Coefficient of linear thermal expansion, longitudinal (23-55)°C	ISO 11359-1/-2	E-6/K	110
Electrical properties			
Relative permittivity (1 MHz)	IEC 60250	-	3.8
Dissipation factor (1 MHz)	IEC 60250	E-4	50
Volume resistivity	IEC 60093	Ohm*m	1E13
Surface resistivity	IEC 60093	Ohm	1E13
Comparative tracking index, CTI, test liquid A	IEC 60112	-	600

Footnotes

- 1) If product name or properties don't state otherwise.
 2) Specimens according to CAMPUS.
 3) The asterisk symbol "*" signifies inapplicable properties.

BASF SE
 67056 Ludwigshafen, Germany