

Product Information

Oct 2016

Ultramid® A3WG6 Polyamide 66


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultramid A3WG6 is a 30% glass fiber reinforced and heat resistance injection molding PA66 grade for machinery components and housings of high stiffness and dimensional stability.

Applications

Typical applications include lamp socket housings, cooling fans, insulating profiles for aluminum window frames, water containers for automotive cooling systems.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.36	
Mold Shrinkage (1/8" bar, in/in)		0.003	
Moisture, %	D-570		
(50% RH)		1.7	
(Saturation)		5.5	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Break, MPa (psi)	D-638		
23°C (73°F)		186 (27,000)	-
Elongation, Break, %	D-638		
23°C (73°F)		3	-
Flexural Modulus, MPa (psi)	D-790		
23°C (73°F)		8,480 (1,230,000)	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
-40°C (-40°F)		91 (1.7)	-
23°C (73°F)		112 (2.1)	-
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, °C(°F)	D-3418	260 (500)	-
Heat Deflection @ 264 psi (1.8 MPa) °C(°F)	D-648	250 (482)	-
Heat Deflection @ 66 psi (.45 MPa) °C(°F)	D-648	250 (482)	-
Coef. of Linear Thermal Expansion, mm/mm °C (in/in °F)	E-831	0.1 X10 ⁻⁴	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 0.71mm	UL94	HB	
Relative Temperature Index, 0.71mm	UL746B		
Electrical, °C		125	
Flammability Rating, 1.5mm	UL94	HB	
Relative Temperature Index, 1.5mm	UL746B		
Mechanical w/o Impact, °C		115	
Mechanical w/ Impact, °C		115	
Electrical, °C		125	
Flammability Rating, 3.0mm	UL94	HB	
Relative Temperature Index, 3.0mm	UL746B		
Mechanical w/o Impact, °C		130	
Mechanical w/ Impact, °C		120	
Electrical, °C		125	
ELECTRICAL	ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm	D-257	1E13	1E10

Processing Guidelines
Material Handling

Max. Water content: 0.15%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level. However 2-4 hours is generally sufficient. Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 280-305°C (536-581°F)

Mold Temperature 80-90°C (176-194°F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

A mold temperature of 80-90°C (176-194°F) is recommended, however temperatures of as low as 45°C (113°F) and as high as 105°C (221°F) can be used where applicable.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

 **BASF**
We create chemistry