

Product Information

Oct 2016

Ultramid® A3Z HP UV BK23220 **Polyamide 66**


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultramid A3Z HP UV BK23220 is an impact modified PA66 containing heat and ultraviolet light stabilizers. Designed for maximum toughness at low temperatures, Ultramid A3Z HP UV BK23220 offers a unique combination of impact performance and excellent processability.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm ³	1183	1.08	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile stress at yield, MPa	527		
23°C		46	-
Nominal strain at break, %	527		
23°C		50	-
Flexural Modulus, MPa	178		
23°C		1,703	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m ²	180		
-40°C		22	-
23°C		83	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	258	-
HDT A, °C	75	63	-

Processing Guidelines
Material Handling

Max. Water content: 0.20%

Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80°C (176°F) is recommended. Drying time is dependent on moisture level, however 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 280-304°C (536-579°F)

Mold Temperature 60-100°C (140-212°F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Back Pressure 0-0.35 MPa (0-50 psi)

Screw Speed 40-80 rpm

Screw Compression Ratio 3:1 to 4:1

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 60-100°C (140-212°F) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

