

Product Information Ultramid®**B35EG3**

07/2015

PA6-GF15**Product description**

Glass fibre reinforced injection moulding grade e.g. for internal gas pressure applications such as steering column switch, automobile mirror housings and wheels of mountain bikes.

Physical form and storage

The product is supplied dry and ready to use in moisture-proof packaging. The material is in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm³. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the perfectly dry material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after some of the material has been withdrawn. Ultramid® can be stored for a longer period of time in dry, well vented rooms without any change to properties. After longer storage times (> 3 months for IBC or > 2 years for bags) or if material from previously opened containers is used, drying is recommended to remove absorbed moisture. Containers stored in cold rooms should be allowed to equalise to normal temperature so that no condensation forms on the pellets.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultramid® B35EG3



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA6-GF15
Density	ISO 1183	kg/m ³	1230
Viscosity number (0.5% in 96 % H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	170
Water absorption, saturation in water at 23°C	similar to ISO 62	%	7.7 - 8.3
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	2.30 - 2.90
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	220
MVR 275 °C/5 kg	ISO 1133	cm ³ /10min	40
Melt temperature, injection moulding/extrusion	-	°C	270 - 290
Mould temperature, injection moulding	-	°C	80 - 90
Moulding shrinkage, constrained ³⁾	-	%	0.55
Flammability			
UL 94 rating at 1,6 mm thickness	IEC 60695-11-10	class	HB
Automotive materials (Thickness >= 1mm) ⁴⁾	FMVSS 302	-	+
Mechanical properties			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	5800 / 3500
Stress at break	ISO 527-1/-2	MPa	130 / 70
Strain at break	ISO 527-1/-2	%	4 / 18
Tensile creep modulus, 1000 h, strain <= 0.5%, 23°C	ISO 899-1	MPa	2100
Flexural modulus	ISO 178	MPa	5200 / 2500
Flexural strength	ISO 178	MPa	180 / 100
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	60 / 105
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	55 / -
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	9 / 25
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	8 / -
Izod notched impact strength (23°C)	ISO 180/A	kJ/m ²	6.5 / 16
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	190
HDT B (0.45 MPa)	ISO 75-1/-2	°C	215
Max. service temperature (short cycle operation)	-	°C	200
Temperature index at 50% loss of tensile strength after 5000 h	IEC 60216	°C	165
Temperature index at 50% loss of tensile strength after 20000 h	IEC 60216	°C	135
Coefficient of linear thermal expansion, longitudinal (23-80)°C	ISO 11359-1/-2	E-6/K	30 - 35
Coefficient of linear thermal expansion, transverse (23-80)°C	ISO 11359-1/-2	E-6/K	70 - 80
Thermal conductivity	DIN 52612-1	W/(m K)	0.34
Specific heat capacity	-	J/(kg*K)	1600
Electrical properties			dry / cond.
Relative permittivity (1 MHz)	IEC 60250	-	3.8 / 7
Dissipation factor (1 MHz)	IEC 60250	E-4	250 / 2400
Volume resistivity	IEC 60093	Ohm*m	1E13 / 1E10
Surface resistivity	IEC 60093	Ohm	1E10
Comparative tracking index, CTI, test liquid A	IEC 60112	-	550

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) Test box with central gating, dimensions of base (107*47*1.5) mm, processing condition: TM = 280°C, TW = 80°C

4) + = passed

BASF SE

67056 Ludwigshafen, Germany