

Product Information Ultramid®
B35G3 bk 564

07/2015

PA6-GF15

Product description

Glass fibre reinforced injection moulding grade e.g. for internal gas pressure applications such as steering column switch, automobile mirror housings and wheels of mountain bikes.

Physical form and storage

The product is supplied dry and ready to use in moisture-proof packaging. The material is in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm³. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the perfectly dry material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after some of the material has been withdrawn. Ultramid® can be stored for a longer period of time in dry, well vented rooms without any change to properties. After longer storage times (> 3 months for IBC or > 2 years for bags) or if material from previously opened containers is used, drying is recommended to remove absorbed moisture. Containers stored in cold rooms should be allowed to equalise to normal temperature so that no condensation forms on the pellets.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultramid® B35G3 bk 564



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA6-GF15
Density	ISO 1183	kg/m ³	1240
Water absorption, saturation in water at 23°C	similar to ISO 62	%	7.7 - 8.3
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	2.30 - 2.90
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	220
Melt temperature, injection moulding/extrusion	-	°C	270 - 290
Mould temperature, injection moulding	-	°C	80 - 90
Moulding shrinkage, constrained ³⁾	-	%	0.5
Flammability			
UL 94 rating at 1,6 mm thickness	IEC 60695-11-10	class	HB
Automotive materials (Thickness >= 1mm) ⁴⁾	FMVSS 302	-	+
Mechanical properties			
			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	6100 / 3200
Stress at break	ISO 527-1/-2	MPa	126 / 67
Strain at break	ISO 527-1/-2	%	2.9 / 13.2
Flexural strength	ISO 178	MPa	189 / 90
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	47 / 107
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	5.9 / 15
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	187
HDT B (0.45 MPa)	ISO 75-1/-2	°C	214
Electrical properties			
			dry / cond.
Comparative tracking index, CTI, test liquid A	IEC 60112	-	550

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) Test box with central gating, dimensions of base (107*47*1,5) mm, processing condition: TM = 280°C, TW = 80°C

4) + = passed

BASF SE

67056 Ludwigshafen, Germany