

Product Information

Oct 2016

Ultramid® B3EG3 BK00564 Polyamide 6


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultramid B3EG3 BK00564 is a 15% glass fiber reinforced, pigmented black injection molding PA6 grade for housings with enhanced impact resistance.

Applications

Typical applications include automotive mirror housings and wheels of mountain bikes.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm³	1183	1.23	
Moisture, %	62		
(50% RH)		2.3	
(Saturation)		7.7	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		6,060	-
Tensile stress at break, MPa	527		
23°C		115	-
Tensile strain at break, %	527		
23°C		2.5	-
Flexural Modulus, MPa	178		
23°C		5,300	-
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m²	180		
-30°C		4.5	-
23°C		5	-
Charpy Notched, kJ/m²	179		
23°C		5	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	220	-
HDT A, °C	75	200	-
HDT B, °C	75	217	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Volume Resistivity (Ohm)	IEC 60093	1E13	1E10
Dielectric Constant (1 MHz)	IEC 60250	3.8	7
Dissipation Factor (100 Hz)	IEC 60250	250	2,400
Dissipation Factor (1 MHz)	IEC 60250	250	2,400

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

