

Product Information

Oct 2016

Ultramid® B3GM35 BKQ642 23220 Polyamide 6


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultramid B3GM35 BKQ642 23220 is a 40% combined glass-fiber and mineral reinforced, pigmented black injection molding PA6 grade.

Applications

Typical applications include industrial articles requiring medium rigidity and high dimensional stability.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.48	
Mold Shrinkage (1/8" bar, in/in)		0.004	
Moisture, %	D-570		
(50% RH)		1.7	
(Saturation)		5.7	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Break, MPa (psi)	D-638		
23°C (73°F)		130 (18,900)	65 (9,430)
Elongation, Break, %	D-638		
23°C (73°F)		2.7	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
-40°C (-40°F)		40 (0.7)	-
23°C (73°F)		53 (1.0)	134 (2.5)
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, °C(°F)	D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) °C(°F)	D-648	200 (392)	-
Heat Deflection @ 66 psi (.45 MPa) °C(°F)	D-648	215 (419)	-
ELECTRICAL	ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm	D-257	>1E13	-

Processing Guidelines
Material Handling

Max. Water content: 0.15%

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C).

Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 270-295°C (518-563°F)

Mold Temperature 80-95°C (176-203°F)

Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95°C (176-203°F) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

 BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

 General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>
