

Product Information

Feb 2016

Ultramid® B3WG7 **Polyamide 6**


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultramid B3WG7 is a 35% glass fiber reinforced injection molding PA6 grade for highly rigid, dimensionally stable components which are resistant to high temperature aging and have improved retention of properties in a hot water environment.

Applications

Typical applications include automotive clutch and accelerator pedals.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm³	1183	1.41	
Moisture, %	62		
(50% RH)		2	
(Saturation)		6.2	
RHEOLOGICAL	ISO Test Method	Dry	Conditioned
Melt Volume Rate (275 °C/5 Kg), cc/10min.	1133	45	-
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		11,000	7,200
Tensile stress at break, MPa	527		
23°C		195	130
Tensile strain at break, %	527		
-40°C		3.8	-
23°C		3.5	7.0
Flexural Modulus, MPa	178		
23°C		10,000	-
IMPACT	ISO Test Method	Dry	Conditioned
Charpy Notched, kJ/m²	179		
-30°C		13	-
23°C		18	33
Charpy Unnotched, kJ/m²	179		
-30°C		90	-
23°C		100	110
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	220	-
HDT A, °C	75	215	-
HDT B, °C	75	220	-
Coef. of Linear Thermal Expansion, Parallel, mm/mm °C		0.18 X10-4	-
Coef. of Linear Thermal Expansion, Normal, mm/mm °C		0.65 X10-4	-
ELECTRICAL	ISO Test Method	Dry	Conditioned
Comparative Tracking Index	IEC 60112	450	450
Volume Resistivity (Ohm)	IEC 60093	1E13	1E10
Dielectric Constant (1 MHz)	IEC 60250	3.9	6.2
Dissipation Factor (100 Hz)	IEC 60250	210	1,900
Dissipation Factor (1 MHz)	IEC 60250	210	1,900
UL RATINGS	UL Test Method	Property Value	
Relative Temperature Index, 0.75mm	UL746B		
Electrical, °C		130	
Flammability Rating, 1.5mm	UL94	HB	
Relative Temperature Index, 1.5mm	UL746B		
Mechanical w/o Impact, °C		130	
Mechanical w/ Impact, °C		90	
Electrical, °C		130	
Flammability Rating, 3.0mm	UL94	HB	
Relative Temperature Index, 3.0mm	UL746B		
Mechanical w/o Impact, °C		130	
Mechanical w/ Impact, °C		100	
Electrical, °C		130	

Processing Guidelines
Material Handling

Max. Water content: 0.15%

Material is supplied in sealed containers and drying prior to molding in a dehumidifying or desiccant dryer is recommended. Drying parameters are dependent upon the actual percentage of moisture in the pellets and typical pre-drying conditions are 2-4 hours at 180F (83C).

Recommended moisture levels for achieving optimum surface qualities and mechanical properties is 0.05% - 0.12%. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet (MSDS), or by contacting your BASF representative.

Typical Profile

Melt Temperature 270-295 degC (518-563 degF)
Mold Temperature 80-95 degC (176-203 degF)
Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 80-95 degC (176-203 degF) is recommended.

Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas. Minimal back pressure should be utilized to prevent glass breakage.

Fill Rate

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

 **BASF**
We create chemistry