

Product Information Ultramid®**B3WGM24 HP bk 23210**

03/2016

PA6-(GF10+M20)**Product description**

Glass-fibre and mineral reinforced injection moulding grade with outstanding flowability for industrial articles having medium to high rigidity, used e.g. for automobile engine covers, housings, etc.

Physical form and storage

The product is supplied dry and ready to use in moisture-proof packaging. The material is in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm³. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the perfectly dry material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after some of the material has been withdrawn. Ultramid® can be stored for a longer period of time in dry, well vented rooms without any change to properties. After longer storage times (> 3 months for IBC or > 2 years for bags) or if material from previously opened containers is used, drying is recommended to remove absorbed moisture. Containers stored in cold rooms should be allowed to equalise to normal temperature so that no condensation forms on the pellets.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultramid® B3WGM24 HP bk 23210



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA6-(GF10+M20)
Density	ISO 1183	kg/m ³	1370
Viscosity number (0.5% in 96 % H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	123
Water absorption, saturation in water at 23°C	similar to ISO 62	%	6.9 - 7.5
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	2.10 - 2.50
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	220
MVR 275 °C/5 kg	ISO 1133	cm ³ /10min	90
Melt temperature, injection moulding/extrusion	-	°C	270 - 290
Mould temperature, injection moulding	-	°C	80 - 90
Molding shrinkage (parallel)	ISO 2577, 294-4	%	0.41
Molding shrinkage (normal)	ISO 2577, 294-4	%	0.59
Mechanical properties			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	8400 / 4000
Stress at break	ISO 527-1/-2	MPa	115 / 55
Strain at break	ISO 527-1/-2	%	2.7 / 9.8
Flexural modulus	ISO 178	MPa	8200 / 3800
Flexural strength	ISO 178	MPa	175 / 90
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	45 / 50
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	40 / 40
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	8 / 15
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	5.5 / 4
Izod notched impact strength (23°C)	ISO 180/A	kJ/m ²	8 / 10
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	190
HDT B (0.45 MPa)	ISO 75-1/-2	°C	215
Max. service temperature (short cycle operation)	-	°C	180
Coefficient of linear thermal expansion, longitudinal (23-80)°C	ISO 11359-1/-2	E-6/K	60 - 110
Coefficient of linear thermal expansion, transverse (23-80)°C	ISO 11359-1/-2	E-6/K	34 - 38
Specific heat capacity	-	J/(kg*K)	1300
Electrical properties			dry / cond.
Relative permittivity (1 MHz)	IEC 60250	-	3.9 / 6.2
Dissipation factor (1 MHz)	IEC 60250	E-4	200 / 2000
Volume resistivity	IEC 60093	Ohm*m	1E13 / 1E10
Surface resistivity	IEC 60093	Ohm	1E10

Footnotes

- 1) If product name or properties don't state otherwise.
 2) The asterisk symbol "*" signifies inapplicable properties.

BASF SE
 67056 Ludwigshafen, Germany