

**Preliminary
Datasheet****Ultramid®****T KR 4340 G6**

03/2016

PA6T/6-GF30 FR**Product description**

Partially aromatic polyamid, halogen-free flame-retardant, light colorable, outstanding flame retardance, resistant to soldering temperatures

Physical form and storage

The product is supplied dry and ready to use in moisture-proof packaging. The material is in the form of cylindrical or flat pellets. Its bulk density is about 0,7 g/cm³. Standard packs are the special 25 kg bag and the 1000 kg bulk container (octagonal IBC=intermediate bulk container made from corrugated board with a liner bag). Subject to agreement other forms of packaging and shipment in tankers by road or rail are also possible. All containers are tightly sealed and should be opened only immediately prior to processing. To ensure that the perfectly dry material delivered cannot absorb moisture from the air the containers must be stored in dry rooms and always carefully sealed again after some of the material has been withdrawn. Ultramid® can be stored for a longer period of time in dry, well vented rooms without any change to properties. After longer storage times (> 3 months for IBC or > 2 years for bags) or if material from previously opened containers is used, drying is recommended to remove absorbed moisture. Containers stored in cold rooms should be allowed to equalise to normal temperature so that no condensation forms on the pellets.

Product safety

In case processing is done under conditions as recommended (cf. processing data sheet) melts are thermally stable and do not generate hazards by molecular degradation or the evolution of gases and vapors. Like all thermoplastic polymers the product decomposes on exposure to excessive thermal load, e.g. when it is overheated or as a result of cleaning by burning off. Further information is available from the safety data sheet.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultramid® T KR 4340 G6



Preliminary Datasheet³⁾

Typical values for uncoloured product at 23 °C ¹⁾	Test method	Unit	Values ²⁾
Properties			
Polymer abbreviation	-	-	PA6T/6-GF30 FR
Density	ISO 1183	kg/m ³	1460
Viscosity number (0.5% in 96 % H ₂ SO ₄)	ISO 307, 1157, 1628	cm ³ /g	120
Water absorption, saturation in water at 23°C	similar to ISO 62	%	4.3 - 5.3
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	1.40 - 1.80
Processing			
Melting temperature, DSC	ISO 11357-1/-3	°C	290
MVR 325 °C/5 kg	ISO 1133	cm ³ /10min	45
Melt temperature, injection moulding/extrusion	-	°C	310 - 330
Mould temperature, injection moulding	-	°C	80 - 120
Molding shrinkage, model-housing 1.5 mm	-	%	0.1
Molding shrinkage (parallel)	ISO 2577, 294-4	%	0.30
Molding shrinkage (normal)	ISO 2577, 294-4	%	0.70
Thermal properties			
Deflection temp. 1.8 (HDT A)	ISO 75-1/-2	°C	220
Flammability (UL-yellow card see attachment)			
GWFI (thickness)	IEC 60695-2-12	°C (mm)	960 (0.4)
GWIT (thickness)	IEC 60695-2-13	°C (mm)	775 (0.4)
Limiting Oxygen Index (LOI)	ISO 4589-1/-2	%	50
Electrical properties			
Relative permittivity (1 MHz)	IEC 60250	-	dry / cond. 3.9 / 4.1
Dissipation factor (1 MHz)	IEC 60250	E-4	150 / 270
Volume resistivity	IEC 60093	Ohm*m	1E15 / 1E14
Surface resistivity	IEC 60093	Ohm	* / 1E14
CTI, solution A	IEC 60112	-	600
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	dry / cond. 11000 / 11000
Stress at break	ISO 527-1/-2	MPa	150 / 130
Strain at break	ISO 527-1/-2	%	2.5 / 2.5
Flexural modulus	ISO 178	MPa	11000 / 11000
Flexural strength	ISO 178	MPa	240 / 210
Charpy unnotched impact strength, 23°C	ISO 179/1eU	kJ/m ²	65 / 50
Charpy unnotched impact strength, -30°C	ISO 179/1eU	kJ/m ²	65 / -
Charpy notched impact strength, 23°C	ISO 179/1eA	kJ/m ²	8.5 / 8
Charpy notched impact strength, -30°C	ISO 179/1eA	kJ/m ²	8 / -

Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "*" signifies inapplicable properties.

3) The typical values of preliminary datasheets are not statistically firm.

BASF SE

67056 Ludwigshafen, Germany

Ultramid® T KR 4340 G6

UL - Yellow Card



Component - Plastics

E41871

BASF SE

Performance Materials Europe, E-PME/NQ - H201, Ludwigshafen 67056 DE

KR4340G6

Polyamide 6/6T (PA6/6T), "Ultramid T"

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	0.40	V-0	1	0	160	115	130
	0.75	V-0	0	0	160	125	140
	1.0	V-0, 5VA	0	0	160	125	140

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): 28

Volume Resistivity (10⁹ohm-cm) : -

High-Voltage Arc Tracking Rate (HVTR): -

High Volt, Low Current Arc Resis (D495): -

Dimensional Stability (%): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2013-06-14
Last Revised: 2015-12-09

© 2016 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.40	V-0 (ALL)
			0.75	V-0 (ALL)
			1.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2016 UL LLC

BASF SE
67056 Ludwigshafen, Germany