

Product Information

Aug 2014

Ultrason[®] E 6020 P PESU (Polyethersulfone)


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultrason E 6020 P is an unfilled, injection molding PESU grade.

Applications

Typical applications include membrane applications and coatings.

PHYSICAL	ISO Test Method	Property Value
Moisture, %	62	
(50% RH)		1
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23°C		2,650
Tensile stress at yield, MPa	527	
23°C		85
Tensile strain at yield, %	527	
23°C		6.9
THERMAL	ISO Test Method	Property Value
HDT A, ° C	75	207

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

 BASF Corporation
 Engineering Plastics
 1609 Biddle Avenue
 Wyandotte, MI 48192

 General Information: 800-BC-RESIN
 Technical Assistance: 800-527-TECH (734-324-5150)
 Web address: <http://www.plasticsportal.com/usa>
