

Product Information Ultrason® E**Ultrason® KR 4113**

08/2013

PESU+PTFE (CF+CD)**Product description**

Compound based on PES with 30 % filler. The filler system, a mixture of carbon fibres, graphite and PTFE powder, considerably improves Ultrason® tribological properties. In addition, this product has a very small expansion coefficient and low tendency to swell in hot oils.

Abbreviated designation according to ISO 1043-1: PESU+ PTFE-(CF+CD)

Physical form and storage

Ultrason® pellets are supplied in bags and/or octabins. The bulk density ranges between 700 and 800 g/l. Provided the packaging remains undamaged, Ultrason® can be stored indefinitely. Ultrason® pellets absorb moisture very rapidly. Therefore, the pellets need to be dried at least 4h at 130 °C to 150 °C in a vacuum or dry air drier prior to processing.

Product safety

From our experience and information, proper treatment and reasonable use of the product will not have any health hazardous effects.

In view of the high temperatures involved in processing Ultrason®, great care must be exercised -even more than for other thermoplastics- in handling the machinery, molds, moldings and residual melts. If there are concerns or doubts on the thermal capacity and limits, the machinery manufacturer should be consulted.

Any product that has decomposed during injection molding must be removed from the barrel by injection into the atmosphere and simultaneous reduction of the barrel temperature. Noxious odors that could form during this procedure can be reduced by rapid cooling of the degraded material, e.g. in a water bath. If the degraded material is not pumped out of the barrel, gas pressure may build up, particularly if nozzle shutoff devices are used. The built-up pressure could then release violently around the nozzle or hopper areas, and explosions would therefore be expected in the course of pumping.

If the normal precautions are taken and the upper temperature limit, i.e. 390°C, is not exceeded, no health hazardous vapors are formed while Ultrason® is being processed. In common with all other thermoplastics, Ultrason® decomposes on exposure to excessive heat, for instance if the melt temperature is too high and/or the residence time in the plasticizing unit is too long or if residues are burned off during cleaning of the machinery. The figures laid down for the maximum allowable dust concentrations (e.g. MAK value in Germany) must be met in further processing.

The work place must be well ventilated, preferably by means of an extraction system installed above the barrel unit. Irrespective of this, all precautions relating to accident prevention must strictly be taken. Under no circumstances may the plasticizing units be dismantled after a breakdown while they are still hot.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

BASF SE
67056 Ludwigshafen, Germany

Ultrason® KR 4113



Product Information

Typical values for uncoloured product at 23 °C ¹⁾	Test method ²⁾	Unit	Values ³⁾
Properties			
Polymer abbreviation	-	-	PESU+PTFE (CF+CD)
Density	ISO 1183	kg/m ³	1480
Viscosity number (in 0,01 g/ml Phenol/1,2, ortho-Dichlorbenzol, 1:1)	ISO 307, 1157, 1628	cm ³ /g	56
Water absorption, equilibrium in water at 23°C	similar to ISO 62	%	1.5
Moisture absorption, equilibrium 23°C/50% r.h.	similar to ISO 62	%	0.50
Glass transition temperature, DSC (10°C/min)	ISO 11357-1/-2	°C	225
Processing			
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	M, E
Melt volume-flow rate MVR 360 °C/10 kg	ISO 1133	cm ³ /10min	10
Melt temperature, injection moulding/extrusion	-	°C	350 - 390
Mould temperature, injection moulding	-	°C	150 - 190
Molding shrinkage, parallel	ISO 2577, 294-4	%	0.31
Molding shrinkage, normal	ISO 2577, 294-4	%	0.46
Mechanical properties			
Tensile modulus	ISO 527-1/-2	MPa	11000
Stress at break	ISO 527-1/-2	MPa	115
Strain at break	ISO 527-1/-2	%	1.5
Charpy unnotched impact strength (23°C)	ISO 179/1eU	kJ/m ²	24
Charpy unnotched impact strength (-30°C)	ISO 179/1eU	kJ/m ²	20
Charpy notched impact strength (23°C)	ISO 179/1eA	kJ/m ²	6.5
Charpy notched impact strength (-30°C)	ISO 179/1eA	kJ/m ²	5
Izod notched impact strength (23°C)	ISO 180/A	kJ/m ²	6.5
Izod notched impact strength (-30°C)	ISO 180/A	kJ/m ²	5.5
Ball indentation hardness at 961 N/30 s	ISO 2039-1	MPa	180
Thermal properties			
HDT A (1.80 MPa)	ISO 75-1/-2	°C	223
Coefficient of linear thermal expansion, longitudinal (23-80°C)	ISO 11359-1/-2	E-6/K	11
Coefficient of linear thermal expansion, longitudinal (180°C)	DIN 53752	E-6/K	13
Electrical properties			
Surface resistivity	IEC 60093	Ohm	4E03
Volume resistivity	IEC 60093	Ohm*m	9E03
Electric strength K20/K20	IEC 60243-1	kV/mm	8

Footnotes

- 1) If product name or properties don't state otherwise.
2) Specimens according to CAMPUS.
3) The asterisk symbol "*" signifies inapplicable properties.

BASF SE
67056 Ludwigshafen, Germany