

Product Information

Oct 2016

Ultrason[®] S 2010 PSU (Polysulfone)


[Email PDF Datasheet](#) | [Print/Save Version](#)
Product Description

Ultrason S 2010 is an unreinforced, medium viscosity standard injection molding PSU grade. It flows readily and offers outstanding heat resistance and dimensional stability. Typical applications include automotive applications such as fuse encapsulation, connectors, heating system and headlight components and household applications requiring high heat resistance.

PHYSICAL	ISO Test Method	Property Value
Density, g/cm ³	1183	1.23
Mold Shrinkage, parallel, %	294-4	0.68
Mold Shrinkage, normal, %	294-4	0.72
Moisture, %	62	
(50% RH)		0.3
(Saturation)		0.8
RHEOLOGICAL	ISO Test Method	Property Value
Melt Volume Rate (360 °C/10 Kg), cc/10min.	1133	90
MECHANICAL	ISO Test Method	Property Value
Tensile Modulus, MPa	527	
23°C		2,550
Tensile stress at yield, MPa	527	
23°C		75
Tensile strain at yield, %	527	
23°C		6
Ball Indentation, MPa	2039-1	135
IMPACT	ISO Test Method	Property Value
Izod Notched Impact, kJ/m ²	180	
-30°C		6
23°C		5.5
Charpy Notched, kJ/m ²	179	
-30°C		6
23°C		5.5
Charpy Unnotched, kJ/m ²	179	
-30°C		N
23°C		N
THERMAL	ISO Test Method	Property Value
HDT A, °C	75	176
Coef. of Linear Thermal Expansion, Parallel, mm/mm °C		0.53 X10-4
ELECTRICAL	ISO Test Method	Property Value
Comparative Tracking Index	IEC 60112	125
Volume Resistivity (Ohm)	IEC 60093	>1E13
Surface Resistivity (Ohm-m)	IEC 60093	>1E15
Dielectric Constant (100 Hz)	IEC 60250	3.1
Dielectric Constant (1 MHz)	IEC 60250	3.1
Dissipation Factor (100 Hz)	IEC 60250	8
Dissipation Factor (1 MHz)	IEC 60250	64
Dielectric Strength, KV/mm	IEC 60243-1	40
UL RATINGS	UL Test Method	Property Value
Flammability Rating, 1.6mm	UL94	HB
Relative Temperature Index, 1.6mm	UL746B	
Mechanical w/o Impact, °C		155
Mechanical w/ Impact, °C		130
Electrical, °C		155
Flammability Rating, 3.2mm	UL94	V-2
Relative Temperature Index, 3.2mm	UL746B	
Mechanical w/o Impact, °C		155
Mechanical w/ Impact, °C		130
Electrical, °C		155

Processing Guidelines
Material Handling

Max. Water content: 0.02%

Ultrason pellets can absorb moisture very rapidly and must be dried before processing. A vacuum or dry air oven operating at 130-150°C (266-302°F) is recommended. Circulating air ovens are unsuitable. Drying time is dependent on moisture level, however the materials must be dried at least 4 hours. Further information concerning safe handling procedures can be obtained from the Safety Data Sheet. Alternatively, please contact your BASF representative.

Typical Profile

Melt Temperature 340-390°C (644-734°F)

Mold Temperature 140-180°C (284-356°F)
Injection and Packing Pressure 35-125 bar (500-1500 psi)

Mold Temperatures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

Back pressure can be utilized to provide uniform melt consistency and reduce trapped air and gas.

Pressures

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing. Surface appearance is directly affected by injection rate.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation
Engineering Plastics
1609 Biddle Avenue
Wyandotte, MI 48192

General Information: 800-BC-RESIN
Technical Assistance: 800-527-TECH (734-324-5150)
Web address: <http://www.plasticsportal.com/usa>

 **BASF**
We create chemistry