



Polypropylene

RC737MO

Description

RC737MO is a random copolymer .

It is designed for blow moulding products with outstanding transparency, clarity and high gloss. This grade also provides high heat distortion temperature, very good impact and good organoleptic properties at improved processability.

CAS-No. 9010-79-1

Applications

Cosmetics
Food packaging

Household applications
Containers for fine chemicals

Special features

Excellent transparency
Improved gloss

Excellent clarity
Good impact behaviour

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	3 g/10min	ISO 1133
Flexural Modulus	950 MPa	ISO 178
Tensile Modulus (50 mm/min)	1.000 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	13 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	27 MPa	ISO 527-2
Charpy Impact Strength, notched (23 °C)	15 kJ/m ²	ISO 179/1eA

Processing Techniques

The actual conditions will depend on the type of equipment used.

Borclear RC737MO is easy to extrude and can be used in all conventional blow moulding machines. To achieve best optical properties optimization of tooling and processing conditions is recommended.

Outstanding transparency can be achieved at a melt temperature of 230°C on a glass peeled mould surface.

Following moulding parameters should be used as guidelines:
Barrel 190 - 220 °C

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

21.11.2013 Ed.2

 Polypropylene
RC737MO

Die
Melt temperature

180 - 220 °C
180 - 220 °C

Storage

RC737MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on compliance to food contact regulations
Recovery and disposal of polyolefins
Information on emissions from processing and fires
Statement on chemicals, regulations and standards

 Polypropylene
RC737MO**Disclaimer**

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.