

PRODUCT DATA SHEET

05.10.2016 Ed.3



Polyethylene HE1106

Description

HE1106 is a fully formulated compound for physical foamed coaxial cable insulations

It is based mainly on high density polyethylene and a nucleating agent to initiate the gas injection foaming process.

Applications

HE1106 is designed to use as physically foamed insulation for:

Small to medium size coaxial cable constructions (type RG)

Specifications

HE1106 meets the following material classification:

ISO 1872-PE, KEGHN, 50-D090
ASTM D 1248 Type III, Category 3

The following cable material standards are met by HE1106:

EN 50290-2-23 ¹

¹ Appropriate parts

Cables manufactured with HE1106 using sound extrusion practice normally comply with the following cable product standards:

IEC 61196

EN 50117

Special Features

HE1106 consists of specially selected components to offer:

Low attenuation over a wide range of frequencies
High expansion degree to slightly above 80%
Broad application window
Uniform cell structure
Smooth surface

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	950 kg/m ³	ISO 1183-1, Method A
Melt Flow Rate (140 °C/5 kg)	7,5 g/10min	ISO 1133-1, Method A
Tensile Strain at Break (50 mm/min)	300 %	ISO 527-2

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



PRODUCT DATA SHEET

05.10.2016 Ed.3



Polyethylene HE1106

Hardness, Shore D (1 s)

60

ISO 868

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Dielectric constant (1 MHz)	2,34	IEC 60250
Dielectric constant (1,9 GHz)	2,34	Borealis Method
Dissipation Factor (1 MHz)	0,00006	IEC 60250
Dissipation Factor (1,9 GHz)	0,00010	Borealis Method

Processing Techniques

HE1106 can be processed over a wide range of conditions. The construction, extruder size and setup of gas injection system all play important roles for selection of proper processing conditions including the extruder temperature profile

The construction, extruder size and setup of gas injection system all play important roles for selection of proper processing conditions including the extruder temperature profile.

At the gas injection point, a temperature of approximately 190°C is recommended for optimal activation of the cell nucleating agent, which is of the exothermic type. Specific recommendations for processing conditions can be determined only when the application and type of equipment are known.

Tooling

Pressure tooling is invariably required. The die diameter is a function of the level of expansion with a greater expansion requiring a smaller die. Typically a die diameter 60% of the nominal insulation outer diameter is used.

Typical extrusion temperatures	
Screw cooling	120°C
Zone 1	160°C
Zone 2	190°C
Zone 3	185°C
Gas Injection	
Zone 4	145°C
Zone 5	135°C
Flange	135°C
Adapter	135°C
Adapter	140°C
Head	130°C

Please contact your local Borealis representative for specific assistance.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

PRODUCT DATA SHEET

05.10.2016 Ed.3

 Polyethylene
HE1106**Packaging**

Package: Bags
 Bulk
 Octabins

Storage

HE1106 should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Safety

The product is not classified as dangerous and is intended for industrial use only. Check and follow local codes and regulations!

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com