

PRODUCT DATA SHEET

05.10.2016 Ed.5



Polyethylene HE3366

Description HE3366

It is a HDPE compound for solid insulation of telephone singles with high extrusion speed. HE3366 is designed as insulation for petroleum filled telephone cables. It is also suitable as outer skin in "foam-skin" constructions.

Specifications

HE3366 meets the following material classification:

ISO 1872-PE, KGHN, 45-D006
ASTM D 1248 Type III, Class A, Category 4, Grade E8, E9

The following cable material standards are met by HE3366:

EN 50290-2-23
DIN VDE 0207, 2Y11

Cables manufactured with HE3366 using sound extrusion practice normally comply with the following cable product standards:

IEC 60708
EN 50407
DIN VDE 0818

Special Features

HE3366 consists of specially selected components to offer:

Low die head pressure

Very good flow behaviour

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	945 kg/m ³	ISO 1183-1, Method A
Melt Flow Rate (190 °C/2,16 kg)	0,7 g/10min	ISO 1133-1, Method A
Tensile Strain at Break	600 %	ISO 527-2
Tensile Strength	23 MPa	ISO 527-2
Oxidation Induction Time (200 °C),	50 min	ISO 11357-6
Brittleness temperature	< -76 °C	ASTM D 746
Environmental Stress Crack Resistance (50 °C, Igepal 10 % F20)	> 48 h	IEC 60811-406
Hardness, Shore D (1 s)	61	ISO 868

For information on the influence of petroleum jelly please refer to the article published on borealisgroup.com : "Impact of Petroleum Jelly on the Ageing of Telephone Wire", by going to the following link

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

PRODUCT DATA SHEET

05.10.2016 Ed.5



Polyethylene HE3366

http://www.borealisgroup.com/pdf/literature/borealis/technical-article/1112Impact_of_Petroleum_Jelly_on_the_Ageing_of_Telephone_Wire_Final.pdf

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Dielectric constant (1 MHz)	2,33	IEC 60250
DC Volume Resistivity	10 PΩcm	IEC 60093
Dielectric Strength	22 kV/mm	IEC 60243
Dissipation Factor (1 MHz)	0,00006	IEC 60250

Processing Techniques

HE3366 can be processed using a wide range of process conditions at very high line speeds (typically up to 2400 m/min).

For normal extrusion equipments and applications, we suggest a melt and conductor preheating temperatures as outlined below. Heated water (up to 50°C) in the first cooling trough has been found beneficial to improve conductor adhesion.

Tooling

Pressure tooling is invariably required. Typically "on size" die diameters are used.

Extrusion

Barrel	165 - 230 °C
Die head	230 °C
Melt temperature	220 - 250 °C
Conductor preheating temperature	100 - 120 °C

Please contact your local Borealis representative for such particulars.

Packaging

Package:	Bags
	Bulk
	Octabins

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

PRODUCT DATA SHEET

05.10.2016 Ed.5

 Polyethylene
HE3366**Safety**

Check and follow local codes and regulations!

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.