

Polyethylene **LE0563**

Thermoplastic Semiconductive Jacketing Compound

Description

LE0563 is a thermoplastic semiconductive compound specifically designed for medium- high and extra-high voltage cable systems requiring improved grounding. It may be used either as a complete jacket or as a thin layer extruded on top of the regular jacket. This compounds permits easy diagnostic testing of the cable to ensure jacket conformity, allowing confirmation of fault-free cable before and after installation. It provides excellent mechanical properties, superior environmental stress crack resistance and good electrical conductivity. Due to the semiconductive properties, it will also provide added protection against lightning.

Specifications

LE0563 meets the applicable requirements as below when processed using sound extrusion practice and testing procedure:

IEC 60502, Type ST7
IEC 60840, Type ST7
IEC 62067, Type ST7

ICEA S-94-649, Type 1
ICEA S-108-720, Type 1
ICEA S-108-720, Type 2

Special features

LE0563 provides excellent environmental stress crack resistance and good electrical conductivity.

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (Compound)	1055 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/21,6 kg)	30 g/10min	ISO 1133
Melt Flow Rate (190 °C/2,16 kg)	0,2 g/10min	ISO 1133
Tensile Strain at Break (25 mm/min) ¹	560 %	ISO 527
Tensile Strength (25 mm/min) ¹	16 MPa	ISO 527
Change of Tensile Properties After Ageing (240 h, 110 °C)	< 25 %	IEC 60811-401
Environmental Stress Crack Resistance (50 °C) (Igepal 10 %), (F0) ¹	> 2.000 h	ASTM D 1693
Hardness, Shore D (1 s) ¹	58	ISO 868
Hardness, Shore D (3 s) ¹	55	ISO 868
Moisture	400 ppm	Karl Fischer-titration
Pressure Test at High Temperature (110 °C, 6 h) ¹	< 5 %	IEC 60811-508

¹ Measured on moulded plaques.

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
DC Volume Resistivity (23 °C) ¹	25 Ohm.cm	ASTM D 991
DC Volume Resistivity (90 °C) ¹	50 Ohm.cm	ASTM D 991

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

 Polyethylene
LE0563

¹ Measured on moulded plaques.

Processing Techniques

To produce a good and reliable cable, it is essential to ensure careful and very clean handling of the jacketing material. Please contact your Borealis representative for more details.

Predrying

It is recommended that LE0563 is dried prior to extrusion. Typical drying conditions are shown below:

Predrying (4 h)	70°C	With dehumidified air
-----------------	------	-----------------------

No screw cooling

Optimum DC volume resistivity and mechanical properties could be obtained by maximizing cooling water temperature or distance between cooling water and die head.

Extrusion

Typical processing temperature ranges for LE0563 are shown below:

Barrel 1	180 °C 356 °F
Barrel 2	190 °C 374 °F
Barrel 3	200 °C 392 °F
Barrel 4	210 °C 410 °F
Barrel 5	210 °C 410 °F
Die	210 °C 410 °F
Melt temperature	215 - 245 °C 419 - 473 °F

Packaging

Package: Smallbins

Safety

The product is not classified as dangerous and is intended for industrial use only. Check and follow local codes and regulations!

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

 Polyethylene
LE0563**Disclaimer**

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.