



Polypropylene

BJ356MO

Description

BJ356MO is a heterophasic copolymer. This grade provides very high melt flow rate, very high stiffness and medium impact strength. and is designed for high-speed injection moulding and contains nucleating and antistatic/demoulding additives.

Components moulded from this grade show good ejectability and combine excellent stiffness with very good gloss, good antistatic and excellent organoleptic properties.

CAS-No. 9010-79-1

Applications

Thin wall containers
Household applications

Technical parts

Special features

High stiffness
Medium impact strength

Excellent antistatic properties
Good gloss

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	100 g/10min	ISO 1133
Flexural Modulus	1.500 MPa	ISO 178
Tensile Modulus (50 mm/min)	1.600 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	4 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	27 MPa	ISO 527-2
Heat Deflection Temperature (0,45 N/mm ²) ¹	105 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	4 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	2,5 kJ/m ²	ISO 179/1eA

¹ Measured on injection moulded specimens acc. to ISO 1873-2

Processing Techniques

This product is easy to process with standard injection moulding machines.

Following moulding parameters should be used as guidelines:

Melt temperature	210 - 260 °C	Minimum to avoid sink marks.
Holding pressure	200 - 500 bar	
Mould temperature	20 - 50 °C	
Injection speed	As high as possible.	

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

 Polypropylene
BJ356MO

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

Storage

BJ356MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Recovery and disposal of polyolefins
Information on emissions from processing and fires
Statement on compliance to food contact regulations

 Polypropylene
BJ356MO**Disclaimer**

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.