



# Polypropylene

## HD214CF

Polypropylene Homopolymer

### Description

**HD214CF** is a homopolymer film resin, suitable for the manufacturing of unoriented film on chill roll process.

### Applications

**HD214CF** is recommended for

Food packaging  
Lamination films  
Stationary films

Flower packaging  
Textile packaging film

### Additives

**HD214CF** contains antiblock but no slip agent

| Additives                     | Content  |                 |
|-------------------------------|----------|-----------------|
| Antiblock (SiO <sub>2</sub> ) | 1800 ppm | Borealis Method |

### Special features

**HD214CF** is optimised to deliver:

High stiffness  
Good mechanical properties  
Easy processability

Heat sterilisable  
Good optical properties

### Physical Properties

| Property                                       | Typical Value | Test Method |
|------------------------------------------------|---------------|-------------|
| Data should not be used for specification work |               |             |
| Melt Flow Rate (230 °C/2,16 kg)                | 8 g/10min     | ISO 1133    |
| Flexural Modulus <sup>1</sup>                  | 1.300 MPa     | ISO 178     |
| Melting temperature (DSC)                      | 162 °C        | ISO 11357-3 |
| Molecular weight distribution                  | Narrow        |             |

<sup>1</sup> Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.



# Polypropylene

## HD214CF

### Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

| Property                                       | Typical Value            | Test Method |
|------------------------------------------------|--------------------------|-------------|
| Data should not be used for specification work |                          |             |
| Instrumented puncture test                     | Total Penetration Energy | 10 J/mm     |
| Haze                                           |                          | < 2,5 %     |
| Gloss at 20 degree (of arc)                    |                          | > 110       |
| Tensile Strain at Break                        | MD                       | 600 %       |
| Tensile Strain at Break                        | TD                       | 700 %       |
| Tensile Strength                               | MD                       | 45 MPa      |
| Tensile Strength                               | TD                       | 35 MPa      |
| Tensile Modulus                                | MD                       | 700 MPa     |
| Tensile Modulus                                | TD                       | 700 MPa     |
| Coefficient of friction (Film/Film)            |                          | 0,40        |
|                                                |                          | ISO 8295    |

### Storage

**HD214CF** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

### Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

### Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

### Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

General statement on compliance to food contact regulations

Statement on polymer additives and BSE

Borealis AG | Wagramerstrasse 17-19 | 1220 Vienna | Austria  
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333  
 FN 269858a | CCC Commercial Court of Vienna | Website [www.borealisgroup.com](http://www.borealisgroup.com)



## Polypropylene HD214CF

### Disclaimer

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.