



Polypropylene HF420FB

Polypropylene Homopolymer

Description

HF420FB is a polypropylene homopolymer intended for fibre applications

Applications

HF420FB is recommended for

Staple fibre
Continuous filaments

Spunbonded nonwovens

Special features

HF420FB is optimised to deliver:

Controlled rheology
High flow
Easy processability
Improved melt stability
Excellent spinning performance on low and high speed technologies

Optimal product consistency
Optimal resin purity
Excellent mechanical properties
Good long term heat stability

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	19 g/10min	ISO 1133
Melting temperature (DSC)	161 °C	ISO 11357-3
Molecular weight distribution	Very narrow	

Storage

HF420FB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

 Polypropylene
HF420FB**Recycling**

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on compliance to food contact regulations
Statement on chemicals, regulations and standards
Statement on polymer additives and BSE

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

www.borealisgroup.com