



Polypropylene

ZP961

Polypropylene Compound

Description

ZP961 is a polypropylene copolymer intended for injection moulding and blow moulding.

Applications

ZP961 has been developed especially for the car industry to be used in automotive exterior parts.

Break fluid reservoirs

Special features

Very good stiffness
Very good dimensional stability

Very good chemical resistance
Very good heat deformation resistance

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	909 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	0,7 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.400 MPa	ISO 178
Flexural Strength	38 MPa	ISO 178
Tensile Strain at Yield (50 mm/min)	3 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	34 MPa	ISO 527-2
Heat Deflection Temperature (0,45 MPa)	95 °C	ISO 75-2
Heat Deflection Temperature (1,8 MPa)	50 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	20 kJ/m ²	ISO 179/1eA
Izod Impact Strength, notched (23 °C)	20 kJ/m ²	ISO 180/1A

Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

Processing Techniques

The actual conditions will depend on the type of equipment used.

The actual conditions will depend on the type of equipment used. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105°C.

Following parameters should be used as guidelines:

 Polypropylene
ZP961

Barrel
Melt temperature
Holding pressure

Mould temperature
Injection speed

200 - 230 °C
190 - 230 °C
50-70% of injection
pressure
20 - 40 °C
Low to medium

Storage

ZP961 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis Brasil S/A | Av. Osvaldo Berto, 700 | Bairro do Pinhal
| Distrito Industrial Alfredo Rela | CEP: 13255-840
| Itatiba - SP | Brasil | Website www.borealisgroup.com