



PolypropyleneTM BorflowTM HL508FB

Polypropylene Homopolymer

Description

Borflow HL508FB is a polypropylene homopolymer intended for fibre applications

Applications

Borflow HL508FB has been developed especially for applications like:

Micro denier fibres at high spinning speeds
Melt blown applications

Special features

Controlled rheology
Easy processability
Optimal product consistency

Very high flow
Perfect suitable for electrostatic charging

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	800 g/10min	ISO 1133
Melting temperature	156 - 160 °C	ISO 3146
Molecular weight distribution	Narrow	

Storage

Borflow HL508FB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our Safety Data Sheet.

Safety

The product is not classified as a dangerous preparation.

Please see our Safety Data Sheet for details on various aspects of safety of the product.

Borflow is a trademark of Borealis A/S, Denmark.

Borealis AG | Wagramerstrasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polypropylene Borflow HL508FB

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Recovery and disposal of polyolefins
Information on emissions from processing and fires
Safety Data Sheet
Statement on compliance to food contact regulations
Statement on chemicals, regulations and standards

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.