



Polyethylene

Borlink™ LE0500

Crosslinkable Semiconductive Compound

Description

Borlink LE0500 is a Supersmooth crosslinkable black polyethylene compound, specially designed for semiconductive conductor screen and bonded insulation screen of energy cables.

Applications

Borlink LE0500 is intended for semiconductive shielding of XLPE extra high voltage (EHV) cables.

Specifications

Borlink LE0500 meets the applicable requirements as below when processed using sound extrusion practices and testing procedures

AEIC CS8	ICEA S-94-649
AEIC CS9	ICEA S-97-682
BS 6622	IEC 60502-2
Cenelec HD 620 S1	IEC 60840
Cenelec HD 632 S1	IEC 62067
DIN VDE 0276-620	NF C33-223
DIN VDE 0276-632	NF C33-226
ICEA S-108-720	UTE C 33-223
ICEA S-93-639	

Special Features

Borlink LE0500 is a ready-to-use Supersmooth semiconductive compound. It offers excellent thermal stability which provides robust cable extrusion and crosslinking at high surface temperature. The excellent distribution of carbon black and additives in Borlink LE0500 results in a superior smoothness of the semiconductive screen.

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1120 kg/m ³	ISO 1183
Tensile Strain at Break (25 mm/min) ¹	180 %	ISO 527
Tensile Strength (25 mm/min) ¹	> 15 MPa	ISO 527
Change of Tensile Properties After Ageing (168 h, 135 °C) ¹	< 20 %	IEC 60811-401
Hot Set Test (200 °C, 0,20 MPa)	Elongation under load 25 % Permanent deformation 0 %	IEC 60811-507
MDR, max torque	14,6 dNm	ISO 6502
Moisture	100 ppm	Karl Fischer-titration

¹ Measured on crosslinked specimens

Borlink is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polyethylene

Borlink LE0500

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
DC Volume Resistivity (23 °C)	25 Ωcm	ISO 3915
DC Volume Resistivity (90 °C)	50 Ωcm	ISO 3915
DC Volume Resistivity (23 °C)	25 Ωcm	ASTM D 991

Processing Techniques

Borlink LE0500 provides excellent surface finish and outstanding output rates, when processing conditions are optimized for the actual processing equipment and cable dimensions. Optimal conditions may vary according to the equipment used. Hence all material handling should preferably be conducted in closed systems and in clean room conditions. Please contact your Borealis representative for more details.

Extrusion

Typical processing temperature ranges for **Borlink LE0500** are shown below:

Hopper drying (4 h)	60 °C	With dehumidified air
Melt temperature	120 - 135 °C	

Packaging

Package: Smallbins

Storage

Borlink LE0500 has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

 Polyethylene
Borlink LE0500**Disclaimer**

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.