



Polypropylene Bormed™ RD804CF

Description

Bormed RD804CF is a random copolymer with low ethylene content.

The current version of Bormed RD804CF has been scheduled for deletion.

Please refer to Bormed RD804CF-11 documentation for new projects.

In case of questions, please contact either your responsible Borealis Sales Manager and/or Application Development Engineer.

This grade is suitable for the manufacturing of non-oriented cast films on chill roll process, blown films on tubular water quenching process as well as injection moulding and ISBM (2-stage process) for ampoules and bottles.

CAS-No. 9010-79-1

Applications

Bormed RD804CF has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of Bormed RD804CF .

Medical device packaging
Pouches for Continuous Ambulatory Peritoneal Dialysis
Parenteral nutrition bags
Pouches for IV solutions
Extension and connection tubings

Secondary packaging
Caps and closures
Bottles/ampoules for injectable solutions
Ampoules/small bottles for eye, ear & nose drops
Bottles for IV-solutions

This grade may only be used for the applications listed in the Product Datasheet and only to the extent that the application is within the scope of the tests set out in the Statement on Compliance to Regulations on Medical Use for that grade. If an application is not listed in the Product Datasheet, the grade can be used for such application only after express written consent of the Borealis Marketing Manager, Healthcare.
Borealis prohibits the use of any healthcare grade product in an implantable device that is introduced into the human body by surgical intervention and that is intended to remain in place following surgical procedure.

Special features

Good optical properties
Good impact strength

High water vapour barrier
Sterilisability by means of water steam

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	8 g/10min	ISO 1133
Flexural Modulus ¹	1.000 MPa	ISO 178
Melting temperature (DSC)	150 °C	ISO 11357-3
Molecular weight distribution	Narrow	

Bormed is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polypropylene

Bormed RD804CF

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property		Typical Value	Test Method
Data should not be used for specification work			
Instrumented puncture test	Total Penetration Energy	17 J/mm	ISO 7765-2
Haze		1,5 %	ASTM D 1003
Gloss at 20 degree (of arc)		> 130	ASTM D 2457
Tensile Strain at Break	MD	550 %	ISO 527-3
Tensile Strain at Break	TD	600 %	ISO 527-3
Tensile Strength	MD	40 MPa	ISO 527-3
Tensile Strength	TD	30 MPa	ISO 527-3
Tensile Modulus	MD	600 MPa	ISO 527-3
Tensile Modulus	TD	600 MPa	ISO 527-3
Coefficient of friction (Film/Film)		> 0,7	ISO 8295

Storage

Bormed RD804CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation with resulting odour generation and colour changes.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

 Polypropylene
Bormed RD804CF

"Safety data sheet" / "Product safety information sheet"
Statement on chemicals, regulations and standards
General statement on compliance to food contact regulations
Statement on compliance to regulations on medical use
Statement on polymer additives and BSE

Disclaimer

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.