

PRODUCT DATA SHEET

08.07.2015 Ed.6


Polypropylene

Fibremod™ GB215HP

Polypropylene, Long Glass Fibre Reinforced

Description

Fibremod GB215HP is a 20 % long glass fibre reinforced polypropylene grade intended for injection moulding and extrusion. The long glass fibres, chemically coupled to the polypropylene matrix, are providing outstanding mechanical properties such as high strength, high stiffness and excellent impact behaviour.

Due to its excellent combination of properties this material can substitute in many applications other engineering plastics or metal alloys. A significant value of this material is the fact that it does not change its mechanical properties at humid conditions or water contact.

The product is available in standard black 9502.

Applications

Fibremod GB215HP has been developed especially for demanding applications in the automotive industry.

Dashboard carriers
Door module carriers

Structural seat parts

Special Features

Fibremod GB215HP is suitable for processing with special foaming technologies.

High heat stabilised

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1040 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	2 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	4.600 MPa	ISO 178
Tensile Strength	105 MPa	ISO 527-2
Heat Deflection Temperature B (0,45 MPa)	154 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	20 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	20 kJ/m ²	ISO 179/1eA

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Application Related and Other Tests

Property	Typical Value	Test Method
Data should not be used for specification work		
Fogging (100 °C,16 h)	< 2 mg	DIN 75201
Emission	< 50 µgC/g	VDA 277

Fibremod is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



PRODUCT DATA SHEET

08.07.2015 Ed.6

 Polypropylene
Fibremod GB215HP**Processing Techniques**

The actual conditions will depend on the type of equipment used.

Injection Moulding

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following parameters should be used as guidelines:

The fibre length in the final part is the key factor determining the mechanical properties. The main goal of the moulding recommendation is to limit fibre breakage to a minimum.

Therefore it is favourable to melt the material as quickly as possible to prevent excessive fibre breakage in the feeding section.

Low work during plastification and smooth flow during moulding provides the most reinforcing fibre structure for the final part.

Further specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borealis representative for specific assistance.

Feeding temperature	40 - 80 °C
Mass temperature	220 - 260 °C
Back pressure	As low as possible
Holding pressure	30 - 60 MPa
Mould temperature	40 - 80 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

Storage

Fibremod GB215HP should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

PRODUCT DATA SHEET

08.07.2015 Ed.6

**Polypropylene****Fibremod GB215HP****Recycling**

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

Regional Availability

Europe

For information on regional availability please contact Borealis Sales Representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com