

PRODUCT DATA SHEET

13.05.2016 Ed.1

Plastomer/Elastomer **Queo™ 7001LA**

Description

Queo 7001LA is an ethylene based octene-1 elastomer, produced in a solution polymerisation process using a metallocene catalyst.

Applications

Demonstrated applications include:

Low SIT Seal layers in lamination and flexible barrier films
 Surface protection film
 Noise reduction in e.g. automotive applications
 Extrusion coating

Cling film
 Halogen free flame retardant compounds
 High strength flexible films

Additives

Queo 7001LA contains a low amount of processing stabilizers.

Special Features

Queo 7001LA is optimised to deliver:

Versatile blending with other polyolefins in film, extrusion and moulding applications.
 Bridging of plastic and elastomeric properties

High clarity
 High flexibility and surface softness
 Low peak melting point

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	870 kg/m ³	ISO 1872-2/ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	1 dg/min	ISO 1133
Flexural Modulus	8 MPa	ISO 527-1
Tensile Stress at Break	7 MPa	ISO 527
Elongation at Break	> 400 %	ISO 527-1
Melting temperature (DSC)	56 °C	ISO 11357-3
Seal Initiation Temperature	< 60 °C	Borealis Method
Vicat softening temperature (10 N)	39 °C	ISO 306
Brittleness temperature	< -90 °C	ISO 974
Izod Impact Strength, notched (23 °C)	No break	ISO 180:2000
Hardness, Shore A	74	ISO 868
Hardness, Shore D	21	ISO 868

Application Related Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Dart Drop	> 40 g/μm	ISO 7765-1
Haze	< 5 %	ASTM D 1003
Gloss	> 100	ISO 2813
Mooney viscosity ML (1+4) 100 °C	30	DIN 53523-3:1976

Queo is a trademark of the Borealis group. Queo is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com




PRODUCT DATA SHEET

13.05.2016 Ed.1

Plastomer/Elastomer

Queo 7001LA



Storage

Queo 7001LA This polymer, like most polymers, is combustible so the usual precautions concerning ignition sources should be taken in warehouses and storage rooms. Where large quantities are kept in store, it is necessary to observe the normal rules for orderly stock control and it is recommended to use the first in – first out (FIFO) principle for stock planning. The products should be stored in a dry and clean facility to prevent contamination and not be exposed to direct sunlight as this may lead to quality deterioration. These materials have a shelf life of at least 3 (three) years after date of production, provided the material remains in its original unopened packaging and are stored under the storage conditions as described in this document. "Shelf life" means that there will not be any substantial difference compared to the agreed specification. The date of batch creation can be derived from the batch code printed on the bags representing. YYMMDDHLL (LL being two letters with no reference to the production time). Borealis Plastomers generally does not sell prime material older than 2 (two) years unannounced. The lower density Queo materials (< 880 kg/m³) are more sensitive to temperatures. Therefore the following specific storage and handling guidelines have to be taken into account

- The product should not be stored for extended periods or transferred at ambient temperatures greatly exceeding 25 degrees Celsius.
- The products should not be stacked when in bags or super sacks

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



PRODUCT DATA SHEET

13.05.2016 Ed.1

 Plastomer/Elastomer
Queo 7001LA**Related Documents**

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on chemicals, regulations and standards
General statement on compliance to food contact regulations
Statement on polymer additives and BSE

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com