

Polyethylene **Visico™ LE0540**

Silane Crosslinkable Semiconductive Compound

Description

Visico LE0540 is a silane crosslinkable black polyethylene compound, specially designed for bonded semiconductive screen applications.

Visico LE0540 is highly suitable for co-extrusion with LDPE silane crosslinkable insulation materials.

Applications

Visico LE0540 is intended for semiconductive applications for silane crosslinkable medium voltage cables with rated voltages up to 36 kV.

Specifications

Cenelec HD620 S2

IEC 60502-2

Special Features

Visico LE0540 a ready-to-use compound, which requires no further addition of a catalyst masterbatch. Visico LE0540 crosslinks via the migration of catalyst from its co-extrusion with silane insulation layer. The excellent distribution of carbon black and additives in Visico LE0540 would result in an outstanding smooth semiconductive screen. Visico LE0540 offers easy and long extrusion performance.

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1080 kg/m ³	ISO 1872-2/ISO 1183
Melt Flow Rate (190 °C/21,6 kg)	25 g/10min	ISO 1133
Tensile Strain at Break (25 mm/min)	250 %	ISO 527
Tensile Strength (25 mm/min)	13 MPa	ISO 527
Strain at Break After Ageing (168 h, 135 °C)	200 %	IEC 60811-401
Hot Set Test (200 °C, 0,20 MPa)	25 %	IEC 60811-507
Moisture	< 300 ppm	Karl Fischer-titration

Visico is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polyethylene

Visico LE0540

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
DC Volume Resistivity (23 °C)	< 100 Ωcm	ISO 3915
DC Volume Resistivity (90 °C)	< 1000 Ωcm	ISO 3915

Processing Techniques

Visico LE0540 provides excellent surface finish and minimal risk for scorch when processing conditions are optimal. The actual conditions will depend on the type of equipment used.

Extrusion

Typical processing temperature ranges for **Visico LE0540** are shown below:

Barrel 2	150 °C	
Barrel 3	150 °C	
Barrel 4	150 °C	
Head	150 °C	
Melt temperature	170 °C	Maximum

Crosslinking

Can be crosslinked by immersion in hot water or exposed to low pressure steam at a temperature in typical circumstances of 70 °C. The time period needed for crosslinking will depend on e.g. the thickness of insulation, type of semiconductive screen and reel size.

Packaging

Package: Smallbins

Storage

Visico LE0540 has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

 Polyethylene
Visico LE0540**Safety**

The product is not classified as dangerous and is intended for industrial use only. Check and follow local codes and regulations!

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.