


Datasheet
Feb/2021

High Density Polyethylene HS5403

Description:

HS5403 is a high density polyethylene, copolymer, exhibits high die swell, good environmental stress cracking resistance (ESCR), good surface quality and high transparency.

Applications:

Tissue and hygiene packaging, Blow molding small volumes, Lubricating oil packaging, Cosmetic packaging

Processes:

Injection blow molding, Extrusion Blow Molding

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	0.30
Density	D 792	g/cm ³	0.954

Typical Properties:

Plaque Properties

Feature	Method	Units	Values
Melt Flow Rate (190°C/21,6kg)	ASTM D 1238	g/ 10 min	26
Tensile Strength at Yield (a)	ASTM D 638	MPa	30
Tensile Strength at Break (a)	ASTM D 638	MPa	35
Flexural Modulus - 1% Secant (b)	ASTM D 790	MPa	1200
Tensile Impact Strength ISO at 23 °C	ISO 8256	kJ/m ²	100
Environmental Stress Cracking Resistance - notch 0,3 mm; 50°C; 10% Igepal CO630 (a)	ASTM D 1693	h/F50	35
Deflection Temperature under Load at 0.455 MPa (b)	ASTM D 648	°C	70

Typical properties correspond to average values obtained in our laboratories. Test specimens prepared from compression molded sheet made according to ASTM D 4703. Thickness of test piece: a) 2 mm; b) 3 mm.

Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.