

**Datasheet**

Mar/2020

Polyethylene IP2418**Description:**

Good processability and flexibility, high melt flow rate and mechanical resistance. No additives added.

Applications:

Blends with EVA for expanded plate, Caps, Flexible injection molded articles

Processes:

Injection Molding

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	ASTM D 1238	g/10 min	24
Density	ASTM D 792	g/cm ³	0.919

Typical Properties - Plaque¹:

Plaque Properties

Feature	Method	Units	Values
Tensile Strength at Yield (a)	ASTM D 638	MPa	9
Tensile Strength at Break (a)	ASTM D 638	MPa	8
Elongation at Break (a)	ASTM D 638	%	160
Flexural Modulus - 1% Secant (b)	ASTM D 790	MPa	300
Shore D Hardness (c)	ASTM D 2240	-	49
Vicat Softening Temperature at 10 N (b)	ASTM D 1525	°C	82

¹ Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break.

Final Remarks¹:

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA - Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
2. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
5. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.
7. Unless specified, Braskem does not recommend the use of this grade for the fabrication of packages, parts or any other type of product designed to medical and/or pharmaceutical applications.
8. The content of this Data Sheet replaces previous revisions published for this product.