


Datasheet

17/01/2019

Linear Low Density Polyethylene SLH118/21
Description:

SLH118/21 is a Linear Low Density Polyethylene developed for tubular blown film extrusion. Films obtained with this product show good processing performance balanced with good optical and elongation properties, as well as very low gel amount.

The minimum biobased carbon content of this grade is 84%, determined according to ASTM D6866.

Additives: slip, antiblock

Applications:

Blends with HDPE, General use packing, Blends with LDPE, Technical films, Technical films for automatic packaging

Processes:

Blown Film Extrusion

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	1
Density	D 792	g/cm ³	0.918

Typical Properties - Films:

Blown Film Properties^a

Feature	Method	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	40/40
Elongation at Break (MD/TD)	D 882	%	1080/1360
Tensile Modulus - 1% Secant (MD/TD)	D 882	MPa	200/210
Dart Drop Impact	D 1709	g/F50	150
Elmendorf Tear Strength (MD/TD)	D 1922	gF	300/510

(a) Film with 38 microns produce in a 40mm extruder and a blow-up ratio of 2.2:1. (MD = extrusion direction and TD = transversal direction).

Final Remarks:

- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- For regulatory information of the product, please refer to Regulatory Document or contact our Technical Assistance Area.
- For information about safety, handling, individual protection, first aids and waste disposal, please refer to MSDS.
- The mentioned values in this report can be changed at any moment without Braskem previous communication.