

Datasheet  
Oct/2020**Polypropylene DP 229C****Description:**

**DP 229C** homopolymer polypropylene is based on the **reverse logistics** of post-consumer packaging with a concentration of **100% recycled material**. This product is **gray suede** in color.

**Processes:**

Injection Molding

**Control Properties**

| Feature                        | Method | Units    | Values |
|--------------------------------|--------|----------|--------|
| Melt Flow Rate (230°C/2.16 kg) | D 1238 | g/10 min | 6.5    |

**Typical Properties<sup>a</sup>**

| Feature                              | Method | Units | Values |
|--------------------------------------|--------|-------|--------|
| Flexural Modulus - 1% Secant         | D 790  | MPa   | 1300   |
| Notched Izod Impact Strength at 23°C | D 256  | J/m   | 35     |

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

**Final Remarks:**

1. Braskem informs this is a recycled product, which composition is not entirely known and may vary, as expected for recycled products. This product has not been tested by Braskem, being client's sole responsibility to verify the product's suitability for the intended use. Braskem is not responsible for any use of this product in discordance with the applicable legislation.
2. Recycled products are not fully regulated, until competent authorities define how such products shall be used, this product is not intended for highly regulated applications, e.g. medical and pharmaceutical applications, contact with food, contact with drinking water, toys and cosmetics. Braskem does not make any warranties of merchantability or suitability of the product for a particular purpose or for a particular sector, sectors not mentioned above are not expressly or implicitly recommended. It is client's sole responsibility to verify the product's suitability for their intended use.
3. The data provided in this document is limited to the extent of Braskem's knowledge and/or supplier's information provided to Braskem on this date. The document herein relates only to the specific Product designated and may not be valid for such Product used in combination with any other product or in any process, unless otherwise specified.