



## Polypropylene FT200WV

Sub-group  
Homopolymer

### Description

Good mold release, nucleated, contains antistat, excellent rigidity and hardness

### Applications

Suggested uses include housewares, caps and closures, fast-cycle injection molding

### Control Properties:

|                                       | ASTM Method | Units    | Values |
|---------------------------------------|-------------|----------|--------|
| Nominal Melt Flow Rate (230°C/2.16kg) | D-1238      | g/10 min | 20     |

### Typical Properties:

|                                                       | ASTM Method | Units          | Values         |
|-------------------------------------------------------|-------------|----------------|----------------|
| Tensile Strength at Yield (2 in/min, 50 mm/min)       | D-638       | psi(MPa)       | 5,600(39)      |
| Elongation at Yield (2 in/min, 50 mm/min)             | D-638       | %              | 8              |
| Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant) | D-790A      | psi(MPa)       | 255,000(1,758) |
| Notched Izod Impact Strength at 23°C                  | D-256A      | ft-lbs/in(J/m) | 0.7(37)        |
| Heat Deflection Temperature at 66 psi                 | D-648B°     | deg F(deg C)   | 257(125)       |
| Rockwell Hardness                                     | D-785       | R              | 104            |

### Final Remarks

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by the Food and Drug Administration. The additives present meet the applicable regulations.
2. This information reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact Technical Service.
5. The values in this report can be modified without prior communication from Braskem.
6. Braskem polyolefin products do not have additives with heavy metals or organotin-based materials.

Revision Date:  
11/22/2013  
[www.braskem.com](http://www.braskem.com)