

**Datasheet**
Review 14 (Dec / 17)**Polypropylene H 604****Description:**

Homopolymer

H 604 is a low melt flow rate polypropylene with high transparency. This resin is designed for thermoforming, blow molding and general extrusion. H 604 exhibits excellent processability, high output, excellent stiffness/impact strength balance, high melt strength, outstanding optical properties and low odor/taste transfer.

Applications:

Corugated sheet and school folder, Food packaging, Sheets, Tissue and hygiene packaging, Transparent packaging

Processes:

Blow Molding, General Extrusion, Thermoforming

Control Properties

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	D 1238	g/10 min	1.5

Typical Properties^a

Feature	Method	Units	Values
Density	D 792	g/cm ³	0.905
Flexural Modulus - 1% Secant	D 790	MPa	1350
Tensile Strength at Yield	D 638	MPa	36
Tensile Elongation at Yield	D 638	%	12
Rockwell Hardness (R Scale)	D 785	-	101
Notched Izod Impact Strength at 23°C	D 256	J/m	50
Deflection Temperature under Load at 0.455 MPa	D 648	°C	101
Deflection Temperature under Load at 1.820 MPa	D 648	°C	57
Vicat Softening Temperature at 10 N	D 1525	°C	146
Haze	1003	%	27

a) Injection molded specimen according to ASTM D 4101.

Final Remarks

1. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
2. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
3. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
4. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS: 9003-07-0.
5. For regulatory information concerning the product, please consult the Regulatory Information Sheet or contact our Technical Assistance Area.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.