

**Datasheet**
Review 2 (Dec / 17)**Polypropylene HP 502N****Description:**

Homopolymer

HP 502N is a homopolymer with average fluidity and high stiffness.

Applications:

Houseware, Plastic furniture, Caps

Processes:

Injection Molding

Control Properties

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	D 1238	g/10 min	11

Typical Properties^a

Feature	Method	Units	Values
Density	D 792	g/cm ³	0.905
Flexural Modulus - 1% Secant	D 790	MPa	1150
Tensile Strength at Yield	D 638	MPa	35
Tensile Elongation at Yield	D 638	%	10
Notched Izod Impact Strength at 23°C	D 256	J/m	24
Deflection Temperature under Load at 0.455 MPa	D 648	°C	96
Vicat Softening Temperature at 10 N	D 1525	°C	151

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

Final Remarks

1. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
2. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
3. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
4. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS: 25895-47-0.
5. The mentioned values in this report can be changed at any moment without Braskem previous communication.
6. For regulatory information concerning the product, please consult the Regulatory Information Sheet or contact our Technical Assistance Area.