


Datasheet
Jan/2021

Polypropylene RPH 0J7 WE

Description:

RPH 0J7 WE polypropylene is based on the **reverse logistics** of post-consumer packaging with a concentration of **100% recycled material**. This product is **white** in color.

Applications:

Caps, Houseware, Garden furniture

Processes:

Injection molding

Control Properties

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	D 1238	g/10 min	10

Typical Properties

Feature	Method	Units	Values
Density	D 792	g/cm ³	0.935
Flexural Modulus - 1% Secant	D 790	MPa	1370
Tensile Strength at Yield	D 638	MPa	33
Tensile Elongation at Yield	D 638	%	10
Rockwell Hardness (R Scale)	D 785	-	95

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

Final Remarks:

- Braskem informs this is a recycled product, which composition is not entirely known and may vary, as expected for recycled products. This product has not been tested by Braskem, being client's sole responsibility to verify the product's suitability for the intended use. Braskem is not responsible for any use of this product in discordance with the applicable legislation.
- Recycled products are not fully regulated, until competent authorities define how such products shall be used, this product is not intended for medical and pharmaceutical applications, food contact, contact with drinking water and toys. Braskem does not make any warranties of merchantability or suitability of the product for a particular purpose or for a particular sector, sectors not mentioned above are not expressly or implicitly recommended. It is client's sole responsibility to verify the product's suitability for their intended use.
- The data provided in this document is limited to the extent of Braskem's knowledge and/or supplier's information provided to Braskem on this date. The document herein relates only to the specific Product designated and may not be valid for such Product used in combination with any other product or in any process, unless otherwise specified.

Final Remarks:

- Braskem informs this is a recycled product, which composition is not entirely known and may vary, as expected for recycled products. This product has not been tested by Braskem, being client's sole responsibility to verify the product's suitability for the intended use. Braskem is not responsible for any use of this product in discordance with the applicable legislation.
- Recycled products are not fully regulated, until competent authorities define how such products shall be used, this product is not intended for medical and pharmaceutical applications, food contact, contact with drinking water and toys. Braskem does not make any warranties of merchantability or suitability of the product for a particular purpose or for a particular sector, sectors not mentioned above are not expressly or implicitly recommended. It is client's sole responsibility to verify the product's suitability for their intended use.
- The data provided in this document is limited to the extent of Braskem's knowledge and/or supplier's information provided to Braskem on this date. The document herein relates only to the specific Product designated and may not be valid for such Product used in combination with any other product or in any process, unless otherwise specified.