


Datasheet

Jan/2021

Linear Low-density Polyethylene WCL L004 SCB

Description:

The linear low-density polyethylene **WCL L004 SCB** is obtained from **reverse logistic** of industrial bags and it has a concentration of **100% recycled material**. This product color is **white**.

Applications:

Blends with HDPE, Liners, Industrial Sacks, Blends with LDPE, Blends with LLDPE, General use packing

Processes:

Blown Film Extrusion, Film Extrusion - General Use

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	ASTM D 1238	g/10 min	0.4
Density	ASTM D 792	g/cm ³	0.925

Typical Properties - Films:

Blown Film Properties^a

Feature	Method	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	24/23
Tensile Strength at Yield (MD/TD)	D 882	MPa	09/11
Dart Drop Impact	D 1709	g/F50	165
Elmendorf Tear Strength (MD/TD)	D 1922	gF	120/646
Secant Modulus 1%	D 882	MPa	199/234

(a) Film with 12,5 microns produce in a 75mm extruder with 1,3 mm of die gap and a blow-up ratio of 4.5:1. (MD = extrusion direction and TD = transversal direction).

Final Remarks:

- Braskem informs this is a recycled product, which composition is not entirely known and may vary, as expected for recycled products. This product has not been tested by Braskem, being client's sole responsibility to verify the product's suitability for the intended use. Braskem is not responsible for any use of this product in discordance with the applicable legislation.
- Recycled products are not fully regulated, until competent authorities define how such products shall be used, this product is not intended for medical and pharmaceutical applications, food contact, contact with drinking water and toys. Braskem does not make any warranties of merchantability or suitability of the product for a particular purpose or for a particular sector, sectors not mentioned above are not expressly or implicitly recommended. It is client's sole responsibility to verify the product's suitability for their intended use.
- The data provided in this document is limited to the extent of Braskem's knowledge and/or supplier's information provided to Braskem on this date. The document herein relates only to the specific Product designated and may not be valid for such Product used in combination with any other product or in any process, unless otherwise specified.