



Polypropylene **INSPIRE 114**

Sub-group

Impact Copolymer

Description

High melt strength, high toughness, excellent processability, high impact and puncture resistance, high film stiffness/machinability, high heat resistance

Applications

Suggested uses include blow film extrusion, sheet extrusion, thermoforming, blow molding

Control Properties:

	ASTM Method	Units	Values
Nominal Melt Flow Rate (230°C/2.16kg)	D-1238	g/10 min	0.5

Typical Properties:

	ASTM Method	Units	Values
Tensile Strength at Yield (2 in/min, 50 mm/min)	D-638	psi(MPa)	4,350(30)
Elongation at Yield (2 in/min, 50 mm/min)	D-638	%	12
Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant)	D-790A	psi(MPa)	215,000(1,482)
Notched Izod Impact Strength at 23°C	D-256A		No Break

Final Remarks

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by the Food and Drug Administration. The additives present meet the applicable regulations.
2. This information reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact Technical Service.
5. The values in this report can be modified without prior communication from Braskem.
6. Braskem polyolefin products do not have additives with heavy metals or organotin-based materials.

Revision Date:
10/5/2012
www.braskem.com