

# CHIMEI

a step up

奇美實業股份有限公司  
717010 台南市仁德區中正路一段 398 號  
+886-6-266-3000  
[www.chimeicorp.com](http://www.chimeicorp.com)

**CHIMEI CORPORATION**  
No. 398 , Sec. 1 , Zhongzheng  
Rd., Rende Dist., Tainan City  
717010 , Taiwan

## Low Residual Monomer SAN KIBISAN® PN-107 L125FG

Product Description: High clarity

| Properties                              | ISO Test Method | Test Condition           | Unit              | PN-107 L125FG            |
|-----------------------------------------|-----------------|--------------------------|-------------------|--------------------------|
| Melt Flow Index                         | 1133            | 220°C×10KG               | ml/10 min         | 58                       |
| Mass Density                            | 1183            | 23 °C                    | g/cm <sup>3</sup> | 1.06                     |
| Tensile Strength                        | 527             | 50 mm/min, yield         | MPa               | 65                       |
|                                         |                 | 50 mm/min, break         | MPa               | 65                       |
| Tensile Elongation                      | 527             | 50 mm/min                | %                 | 4                        |
| Flexural Strength                       | 178             | 2 mm/min                 | MPa               | 89                       |
| Flexural Modulus                        |                 | 2 mm/min                 | GPa               | 2.6                      |
| Izod Impact Strength                    | 180/1A          | 23°C, Notched            | KJ/m <sup>2</sup> | 2                        |
|                                         |                 | -30°C, Notched           | KJ/m <sup>2</sup> | –                        |
| Charpy Impact Strength                  | 179             | 23°C, Notched            | KJ/m <sup>2</sup> | 2                        |
|                                         |                 | Charpy<br>-30°C, Notched | KJ/m <sup>2</sup> | –                        |
| Vicat Softening Temp.                   | 306             | 50°C/hr;1KG              | °C                | 104                      |
|                                         |                 | 50°C/hr;5KG              | °C                | 101                      |
| Heat Distortion Temp.                   | 75/A            | 1.8MPa, unannealed       | °C                | 88                       |
|                                         |                 | 1.8MPa, annealed         | °C                | 99                       |
| Coefficient of Linear Thermal Expansion | 11359           | -                        | -                 | 3.6~3.8*10 <sup>-5</sup> |
| Flammability                            | -               | UL-94                    | -                 | 1.5mm HB                 |
| Mold Shrinkage                          | 294-4           | -                        | %                 | 0.2~0.7                  |
| Symbol                                  | 1043            | -                        | -                 | >SAN<                    |

July 22, 2021

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own test

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHI MEI CORPORATION at the date of issue. CHI MEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHI MEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHI MEI CORPORATION. In no event will CHI MEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.