

Product Datasheet



Enable™ 2010CB Wire & Cable

Performance Polymer

Product Description

Enable™ 2010CB performance polymer resin is an ethylene 1-hexene copolymer. It is an excellent blend partner in halogen-free flame retardant compounds, LV silane cross-linkable insulation and cable jacketing to enhance mechanical properties such as tensile strength, elongation, tear and crack resistance. It combines good processability and provides melt strength for improved dimensional stability. Sufficient Cu-inhibitor should be added to meet specific aging requirements in insulation. For jacketing applications, addition of carbon black or UV stabilizer is required.

General

Availability ¹	- Africa & Middle East - Asia Pacific	- Europe - Latin America	North America
Additive	Thermal Stabilizer: Yes		
Applications	- Communication Cable - Halogen-free flame retardant (HFFR) compounds	- High Voltage Jacketing - Low Voltage Jacketing	- LV silane cross-linkable insulation - Medium Voltage Jacketing
Form(s)	Pellets		
Revision Date	04/01/2019		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.920 g/cm ³	0.920 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	1.0 g/10 min	1.0 g/10 min	ASTM D1238
Peak Melting Temperature	237 °F	114 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	226 °F	108 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 20 in/min (510 mm/min)	1900 psi	13 MPa	ASTM D638
Tensile Strength at Break 20 in/min (510 mm/min)	4200 psi	29 MPa	ASTM D638
Elongation at Yield (20 in/min (510 mm/min))	10 %	10 %	ASTM D638
Elongation at Break (20 in/min (510 mm/min))	670 %	670 %	ASTM D638
Flexural Modulus - 1% Secant (0.051 in/min (1.3 mm/min))	35000 psi	240 MPa	ASTM D790A
Durometer Hardness (Shore D, 15 sec)	50	50	ASTM D2240

Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Volume Resistivity (500 V)	2.2E+15 ohms·m	2.2E+15 ohms·m	IEC 62631-3-1
Relative Permittivity (1 MHz)	2.29	2.29	IEC 62631-2-1
Dissipation Factor (1 MHz)	2.4E-4	2.4E-4	IEC 62631-2-1

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Specimens were compression molded in accordance with ASTM D 4703, Procedure C.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Product Datasheet

ExxonMobil**Enable™ 2010CB Wire & Cable**
Performance PolymerFor additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com