

Product Datasheet



Exact™ 4006

Ethylene-based Plastomer Resin

Product Description

Exact™ 4006 is an ethylene 1-butene plastomer produced using ExxonMobil Chemical's EXXPOL® Technology. This resin is designed for specialty applications requiring moderate flow. This resin is supplied with a primary antioxidant for protection against thermal oxidation.

General

Availability ¹	▪ Latin America	▪ North America
Additive	▪ Thermal Stabilizer: Yes	
Applications	▪ Wire and Cable Compounds	
Form(s)	▪ Pellets	
Revision Date	▪ 04/01/2020	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.880 g/cm ³	0.880 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	10 g/10 min	10 g/10 min	ASTM D1238
Peak Melting Temperature	149 °F	65 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	109 °F	43.0 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break ² 2.0 in/min (50 mm/min)	> 1400 psi	> 9.5 MPa	ExxonMobil Method
Elongation at Break ² (2.0 in/min (50 mm/min))	> 800 %	> 800 %	ExxonMobil Method
Flexural Modulus - 1% Secant Procedure A, 0.051 in/min (1.3 mm/min)	3100 psi	21 MPa	ExxonMobil Method
Procedure B, 0.51 in/min (13 mm/min)	3500 psi	24 MPa	
Environmental Stress-Crack Resistance 10% Igepal, F0	> 1000 hr	> 1000 hr	ExxonMobil Method
Durometer Hardness Shore A, 15 sec	79	79	ExxonMobil Method
Shore D, 15 sec	20	20	

Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Dielectric Constant (1 MHz)	2.1	2.1	ExxonMobil Method
Dissipation Factor (1 MHz)	1E-2	1E-2	ExxonMobil Method

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

- Physical properties were measured on compression molded specimens based on ASTM D4703C.
- Tensile testing was conducted at a crosshead speed of 2 in/min.
- Dielectric constant and dissipation factor were measured using the micrometer electrode method with a 75 mil, 2" circular disc.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² All specimens reached extension limit, did not break.

Product Datasheet

ExxonMobilExact™ 4006
Ethylene-based Plastomer ResinFor additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com