

Product Datasheet



ExxonMobil™ LLDPE LL 1236 Series

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LL 1236 Series are ethylene 1-butene linear low density polyethylene resins with increased stiffness and a higher melt index. These resins can be used alone or as a component in blown or cast packaging and industrial film.

General

Availability ¹	- Latin America - North America
Additive	- LL 1236.85: Antiblock: No; Slip: 400 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes - LL 1236.86: Antiblock: 6000 ppm; Slip: 1500 ppm; Processing Aid: Yes; Thermal Stabilizer: Yes - LL 1236.84: Antiblock: No; Slip: 400 ppm; Processing Aid: No; Thermal Stabilizer: Yes
Applications	- Blown Film - Bread Bags - Cast Film - Food Packaging - Packaging Films - Paper Overwrap - Zipper Bag
Form(s)	Pellets
Revision Date	06/11/2020

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.925 g/cm ³	0.925 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	3.6 g/10 min	3.6 g/10 min	ASTM D1238
Peak Melting Temperature	253 °F	123 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	212 °F	100 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1500 psi	10 MPa	ASTM D882
Tensile Strength at Yield TD	1500 psi	10 MPa	ASTM D882
Tensile Strength at Break MD	5800 psi	40 MPa	ASTM D882
Tensile Strength at Break TD	3600 psi	25 MPa	ASTM D882
Elongation at Break MD	530 %	530 %	ASTM D882
Elongation at Break TD	810 %	810 %	ASTM D882
Secant Modulus MD - 1% Secant	30000 psi	200 MPa	ASTM D882
Secant Modulus TD - 1% Secant	33000 psi	220 MPa	ASTM D882
Dart Drop Impact	< 60 g	< 60 g	ASTM D1709A
Elmendorf Tear Strength MD	30 g	30 g	ASTM D1922
Elmendorf Tear Strength TD	280 g	280 g	ASTM D1922
Puncture Force	6 lbf	28 N	ExxonMobil Method
Puncture Energy	14 in-lb	1.6 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss	91	91	ASTM D2457
Haze	2.3 %	2.3 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (0.8 mil / 20 micron) made from LL 1236.85 resin on a 3.5 inch cast film line with a 8.25 in (21 cm) melt curtain, 80°F (27°C) chill roll temperature at a 365 ft/min (111 m/min) take-off speed and a melt temperature of 527°F (275°C).

Product Datasheet

**ExxonMobil™ LLDPE LL 1236 Series**
Linear Low Density Polyethylene Resin**Notes**

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com