

## Product Datasheet



# Vistamaxx™ Performance Polymer 3588FL

## Propylene Elastomer

### Product Description

Vistamaxx 3588FL is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology. The 'FL' designates this product passes ExxonMobil's test for film appearance with regard to gels, as needed for performance film applications ('A' rating).

### Key Features

- Pure sealant layer of co-extruded structures in BOPP and cast PP film applications for low seal initiation temperature, high seal strength and enhanced seal integrity.
- RoHS compliant.

### General

|                           |                                                                                                      |                                                                                     |                                                                   |
|---------------------------|------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------|
| Availability <sup>1</sup> | <ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> </ul> | <ul style="list-style-type: none"> <li>• Europe</li> <li>• Latin America</li> </ul> | <ul style="list-style-type: none"> <li>• North America</li> </ul> |
| Applications              | <ul style="list-style-type: none"> <li>• Cast Film</li> </ul>                                        |                                                                                     |                                                                   |
| Uses                      | <ul style="list-style-type: none"> <li>• Film</li> </ul>                                             | <ul style="list-style-type: none"> <li>• Packaging</li> </ul>                       |                                                                   |
| RoHS Compliance           | <ul style="list-style-type: none"> <li>• RoHS Compliant</li> </ul>                                   |                                                                                     |                                                                   |
| Form(s)                   | <ul style="list-style-type: none"> <li>• Pellets</li> </ul>                                          |                                                                                     |                                                                   |
| Revision Date             | <ul style="list-style-type: none"> <li>• 07/14/2020</li> </ul>                                       |                                                                                     |                                                                   |

| Physical                                               | Typical Value (English) | Typical Value (SI)      | Test Based On     |
|--------------------------------------------------------|-------------------------|-------------------------|-------------------|
| Density <sup>2</sup>                                   | 0.889 g/cm <sup>3</sup> | 0.889 g/cm <sup>3</sup> | ExxonMobil Method |
| Melt Mass-Flow Rate (MFR) <sup>2</sup> (230°C/2.16 kg) | 8.0 g/10 min            | 8.0 g/10 min            | ExxonMobil Method |
| Ethylene Content                                       | 4 wt%                   | 4 wt%                   | ExxonMobil Method |

| Hardness                     | Typical Value (English) | Typical Value (SI) | Test Based On     |
|------------------------------|-------------------------|--------------------|-------------------|
| Durometer Hardness (Shore D) | 50                      | 50                 | ExxonMobil Method |

| Mechanical                   | Typical Value (English) | Typical Value (SI) | Test Based On     |
|------------------------------|-------------------------|--------------------|-------------------|
| Tensile Stress at 300%       | 1700 psi                | 12 MPa             | ExxonMobil Method |
| Tensile Strength at Yield    | 2400 psi                | 16 MPa             | ExxonMobil Method |
| Tensile Strength at Break    | 3800 psi                | 26 MPa             | ExxonMobil Method |
| Tensile Stress at 100%       | 1600 psi                | 11 MPa             | ExxonMobil Method |
| Elongation at Yield          | 20 %                    | 20 %               | ExxonMobil Method |
| Elongation at Break          | 637 %                   | 637 %              | ExxonMobil Method |
| Flexural Modulus - 1% Secant | 58000 psi               | 400 MPa            | ExxonMobil Method |

| Elastomers            | Typical Value (English) | Typical Value (SI) | Test Based On     |
|-----------------------|-------------------------|--------------------|-------------------|
| Tear Strength (Die C) | 724 lbf/in              | 127 kN/m           | ExxonMobil Method |

| Thermal                     | Typical Value (English) | Typical Value (SI) | Test Based On     |
|-----------------------------|-------------------------|--------------------|-------------------|
| Vicat Softening Temperature | 217 °F                  | 103 °C             | ExxonMobil Method |

### Additional Information

Please contact Customer Service for food law compliance information.

## Product Datasheet

**Vistamaxx™ Performance Polymer 3588FL**  
Propylene Elastomer**Legal Statement**

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

**Processing Statement**

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Property specified in conventional unit of measure.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)