

Product Datasheet



Vistamaxx™ Performance Polymer 6000

Propylene Elastomer

Product Description

Vistamaxx 6000 performance polymer is a metallocene catalyzed copolymer.

Key Features

- When used as the functional layer(s) in cast stretch film, it provides enhanced ultimate stretch, improved holding force and exceptional tear propagation resistance combined with excellent processability. In demanding wrapping operations this enables improved load stability and reduced film breaks.
- These superior properties make this resin an excellent fit in thin gauge high performance cast stretch films, including power pre-stretch films.

General

Availability ¹	- Africa & Middle East - Asia Pacific	- Europe - Latin America	North America
Applications	Cast Stretch Film		
Uses	Film	Packaging	
RoHS Compliance	RoHS Compliant		
Revision Date	07/14/2020		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.889 g/cm ³	0.889 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	3.7 g/10 min	3.7 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Peak Melting Temperature	222 °F	105 °C	ExxonMobil Method
Peak Crystallization Temperature	148 °F	64 °C	ExxonMobil Method

Films	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	2200 psi	15 MPa	ExxonMobil Method
Tensile Strength at Yield TD	1900 psi	13 MPa	ExxonMobil Method
Tensile Strength at Break MD	9100 psi	60 MPa	ExxonMobil Method
Tensile Strength at Break TD	5200 psi	36 MPa	ExxonMobil Method
Elongation at Break MD	440 %	440 %	ExxonMobil Method
Elongation at Break TD	790 %	790 %	ExxonMobil Method
Secant Modulus MD - 1% Secant	42000 psi	290 MPa	ExxonMobil Method
Secant Modulus TD - 1% Secant	47000 psi	330 MPa	ExxonMobil Method

Optical	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	89	89	ASTM D2457
Haze	0.4 %	0.4 %	ExxonMobil Method

Additional Information

Please contact Customer Service for food law compliance information.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Product Datasheet

**Vistamaxx™ Performance Polymer 6000**
Propylene Elastomer**Processing Statement**

The film properties have been measured on a film (1 mil/25 micron) made from Vistamaxx 6000 on a Black Clawson 3.5 inch cast line at a 6.25" melt curtain length, 425 °F melt temperature, 56 °F chill roll temperature and 180 fpm line speed. Films were aged at 77°F for 40 hours before lab aging and testing.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com