


Formosa Plastics®
Formolene® PP

Formolene® 3302B

Random Copolymer for Extrusion and Thermoforming Applications

Formolene® 3302B is a low melt flow, random copolymer polypropylene with good clarity, fast cycle time and easy mold release, designed for extrusion processing and thermoforming.

The use of an advanced nucleator provides the desirable aesthetic values of neutral color and low haze. It also provides fast crystallinity speed and uniform, isotropic shrinkage which enables fast forming.

Formolene® 3302B meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the “Products” section on our website (<http://www.fpcusa.com/ourproducts.html>).

This material is free of animal-derived content.

Typical Properties of this Commercial Grade

Property	Test Method	Typical values	
		English	SI
Melt Flow Rate, I ₂ @ 230°C	ASTM D1238	2.3 g/10min	2.3 g/10min
Density	ASTM D1505	0.9 g/cm ³	0.9 g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	4,300 psi	30 MPa
Elongation at Yield (50 mm/min)	ASTM D638	13 %	13 %
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D 790	160,000 psi	1100 MPa
Notched Izod Impact Strength @ 73°F	ASTM D256A	3.0 ft-lb/in	160 J/m
Plaque Haze, %	FPC method	24 %	24 %

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.

Data for representative purposes only; not to be construed as product specification.

Published 12/08, Revised 07/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA