


Formosa Plastics®
Formolon® PVC

Formolon®-265

PVC Copolymer Blending Resin

F-265 is a fine particle size polyvinyl chloride vinyl acetate copolymer plastisol blending resin. The product has been designed for use in application where rapid gelation and fusion is a requirement, due to low processing temperatures.

When used in combination with copolymer dispersion resin, F-265 has been successfully used in carpet backing, automotive sealants and underbody coatings as well as walk-off mats.

TYPICAL RESIN PROPERTIES

Relative Viscosity	ASTM D2857	1.95
Inherent Viscosity	ASTM D1243	0.77
K-Value	Fikentscher's Constant	59
Vinyl Acetate Content %	QC-10-105	5.0
Bulk Density	ASTM D1895 (A)	0.55 g/cc
Volatiles	ASTM D3030	0.3%
Sieve Analysis	ASTM1921(B)	
Through 40 Mesh Screen		100 %
Through 200 Mesh Screen		99 %
Average Particle Size	Coulter Counter LS230	35 micron

NOTE: The physical data presented above are typical values and should not be construed as a specification.

Originally Published 04/01/2002, Revised 09/06/2019

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

©Formosa Plastics Corporation, U.S.A.

Formolon® is a registered trademark of FPC USA