


Formosa Plastics®
Formolon® PVC

Formolon® -KVH

PVC Homopolymer Dispersion Resin

F-KVH is a high molecular weight PVC homopolymer dispersion resin which imparts pseudoplastic flow where it is used. Plastisol prepared utilizing F-KVH is particularly suited for dip, slush and rotational molding where mold release and pseudoplasticity is desired as well as fabric coating applications where minimum strike through is essential.

TYPICAL RESIN PROPERTIES

Relative Viscosity	ASTM D2857	2.65
Inherent Viscosity	ASTM D1243	1.17
K-Value	Fikentscher's Constant	75
Volatiles	ASTM D3030	0.3%
Methanol extract	ASTM D2222	1.5 %

TYPICAL PLASTISOL¹ PROPERTIES

Brookfield Viscosity	ASTM D1824	2 rpm aged 2 hrs	5000 poise
		20 rpm aged 2 hrs	650 poise
Severs Viscosity	ASTM D1823	100 psig aged 2 hrs	110 poise
Gelation Temperature			184 °F

500 gm resin and 300 gm DOP, Hobart mixer mixed 5 min. @ No. 1 speed and 10 min. @ No. 2 speed, undeaerated

NOTE: The physical data presented above are typical values and should not be construed as a specification.

Originally Published 05/31/1981, Revised 09/06/2019.

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

©Formosa Plastics Corporation, U.S.A.

Formolon® is a registered trademark of FPC USA

09/19