

# 台塑聚丙烯塑膠 FORMOSA POLYPROPYLENE



## 永嘉烯 YUNGSOX

## 2100M

### 均聚物 HOMOPOLYMER

#### 用途 Applications

- CPP 鑄膜 CPP film
- 電鍍積層膜  
Aluminum metallized cast film

#### 特性 Characteristics

- 電鍍性佳 Good metallizing properties
- 透明性優 Excellent transparency
- 積層加工性優 Excellent laminates

#### 物性 Typical Properties

| 項目<br>Properties                      | 單位<br>Unit         | 檢驗方法<br>Test Method | 平均值<br>Typical Value |
|---------------------------------------|--------------------|---------------------|----------------------|
| 熔融指數<br>Melt Index                    | g/10min            | ISO1133             | 7                    |
| 密度<br>Density                         | g/cm <sup>3</sup>  | ISO1183             | 0.90                 |
| 熔點<br>Melting Point                   | °C                 | DSC                 | 165                  |
| 熱變形溫度<br>Heat Deflection Temperature  | °C                 | ISO75               | 115                  |
| 軟化點溫度<br>Vicat Softening Temperature  | °C                 | ISO306              | 155                  |
| 降伏點拉力強度<br>Tensile Strength at Yield  | Kg/cm <sup>2</sup> | ISO527              | 350                  |
| 斷裂點伸長率<br>Tensile Elongation at Break | %                  | ISO527              | 500                  |
| 洛氏硬度<br>Rockwell Hardness             | R scale            | ISO2039             | 107                  |
| 剛性係數<br>Flexural Modulus              | Kg/cm <sup>2</sup> | ISO178              | 14,000               |
| IZOD 衝擊強度<br>IZOD Impact Strength     | Kg.cm/cm notch     | ISO 180             | 23°C<br>4.0          |
|                                       |                    |                     | -20°C<br>---         |
| 收縮率<br>Mold Shrinkage                 | %                  | FPC Method          | 1.3-1.7              |
| 濁度<br>Haze (30μ)                      | %                  | FPC Method          | < 0.5                |

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

#### FDA 認可 FDA Approval

永嘉烯 2100M 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 2100M resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

Jan 2015

技術服務 Client service

電話 TEL: 886-7-6419911 ext. 313

傳真 FAX: 886-7-6425581